



SPECIFICATION FOR
TDK MULTILAYER CERAMIC CHIP CAPACITORS

NAME OF COMPANY	DWG. NO.
TDK ITEM C0603, C1005, C1608, C2012, C3216, C3225, C4532, C5750 Type / 6.3V to 630V C0G, X5R, X7R, Y5V Characteristics	DATE ISSUED

TDK ENGINEERING SIGNATURE

DRAWN BY	CHECKED BY	APPROVED BY
DATE	DATE	DATE

Please return this specification to TDK representatives with your signature.

If orders are placed without returned specification, please allow us to judge that specification is accepted by your side.

CUSTOMER RESPONSE

Please check one of three conditions below.

- Approval
- Approval with the following changes
- Reject with the following reasons

NAME OF COMPANY	SIGNATURE	DATE
-----------------	-----------	------

TDK CORPORATION
13-1,Nihonbashi 1-chome,Chuo-ku,Tokyo 103-8272,Japan
Phone:Tokyo(03)3278-5111

1. SCOPE

This specification is applicable to chip type multilayer ceramic capacitors with a priority over the other relevant specifications.

Production places defined in this specification shall be TDK Corporation Japan, TDK Taiwan Corporation, TDK Xiamen Co.,Ltd, TDK(Suzhou)Co.,Ltd, TDK Korea Corporation, TDK(Malaysia)Sdn.Bhd, TDK Components U.S.A. Inc, and TDK Hungary Ltd.

EXPLANATORY NOTE:


This specification warrants the quality of the ceramic chip capacitors. The chips should be evaluated or confirmed a state of mounted on your product.

If the use of the chips goes beyond the bounds of the specification, we can not afford to guarantee.

2. CODE CONSTRUCTION

(Example)	<u>C2012</u>	<u>X7R</u>	<u>1E</u>	<u>105</u>	<u>K</u>	<u>T</u>
	(1)	(2)	(3)	(4)	(5)	(6)

(1) Type



Type	Typical Dimensions (Unit : mm)				
TDK (EIA style)	L	W	T	B	G
C0603 (CC0201)	0.60 ± 0.03	0.30 ± 0.03	0.30 ± 0.03	0.10 - 0.20	0.20 min.
C1005 (CC0402)	1.00 ± 0.05	0.50 ± 0.05	0.50 ± 0.05	0.10 min.	0.30 min.
C1608 (CC0603)	1.60 ± 0.10	0.80 ± 0.10	0.80 ± 0.10	0.20 min.	0.30 min.
C2012 (CC0805)	2.00 ± 0.20	1.25 ± 0.20	1.25 ± 0.20	0.20 min.	0.50 min.
C3216 (CC1206)	3.20 ± 0.20	1.60 ± 0.20	1.60 ± 0.20	0.20 min.	1.00 min.
C3225 (CC1210)	3.20 ± 0.40	2.50 ± 0.30	2.50 ± 0.30	0.20 min.	-
C4532 (CC1812)	4.50 ± 0.40	3.20 ± 0.40	2.50 ± 0.30	0.20 min.	-
C5750 (CC2220)	5.70 ± 0.40	5.00 ± 0.40	2.50 ± 0.30	0.20 min.	-

* As for each item, please refer to the table A in the end of the specification

(2) Temperature Characteristics (Details are shown in table 1 No.6 and No.7 at page 6)

(3) Rated Voltage

Symbol	Rated Voltage
2 J	DC 630 V
2 E	DC 250 V
2 A	DC 100 V
1 H	DC 50 V
1 E	DC 25 V
1 C	DC 16 V
1 A	DC 10 V
0 J	DC 6.3 V

(4) Rated Capacitance

Stated in three digits and in units of pico farads (pF).

The first and Second digits identify the first and second significant figures of the capacitance, the third digit identifies the multiplier.

R is designated for a decimal point.

Example 2R2 → 2.2pF
105 → 1,000,000pF

(5) Capacitance tolerance

Symbol	Tolerance	Capacitance
C	± 0.25 pF	10pF and under
D	± 0.5 pF	
J	± 5 %	Over 10pF
K	± 10 %	
M	± 20 %	
Z	+80, -20%	

(6) Packaging

Symbol	Packaging
B	Bulk
T	Taping

3. RATED CAPACITANCE AND TOLERANCE

3.1 Standard combination of rated capacitance and tolerances

Class	Temperature Characteristics	Capacitance tolerance		Rated capacitance
1	C0G	10pF and under	C ($\pm 0.25\text{pF}$)	0.5, 1, 1.5, 2, 2.2, 3, 3.3, 4, 4.7, 5
			D ($\pm 0.5\text{pF}$)	6, 6.8, 7, 8, 9, 10
		12pF to 10,000pF	J ($\pm 5\%$) K ($\pm 10\%$)	E – 12 series
		Over 10,000pF	K ($\pm 10\%$)	E – 6 series
2	X5R X7R	10uF and under	K ($\pm 10\%$) *1	E – 6 series
		Over 10uF	M ($\pm 20\%$)	
	Y5V	0.1uF and under	Z (+80, -20%)	E – 1 series
		Over 0.1uF		E – 3 series

*1 The standard capacitance tolerance for C1005X5R0J155, C1005X5R0J225 and C1608X5R0J106 is M ($\pm 20\%$).

3.2 Capacitance Step in E series

E series	Capacitance Step									
E- 1	1.0									
E- 3	1.0			2.2			4.7			
E- 6	1.0		1.5		2.2		3.3		4.7	
E-12	1.0	1.2	1.5	1.8	2.2	2.7	3.3	3.9	4.7	5.6
									6.8	8.2

4. OPERATING TEMPERATURE RANGE

T.C.	Min. operating Temperature	Max. operating Temperature	Reference Temperature
X5R	-55°C	85°C	25°C
Y5V	-30°C	85°C	25°C
X7R C0G	-55°C	125°C	25°C

5. STORING CONDITION AND TERM

5 to 40°C at 20 to 70%RH

6 months Max.

6. P.C. BOARD

When mounting on an aluminum substrate, large case sizes such as C3225, C4532 and C5750 types are more likely to be affected by heat stress from the substrate. Please inquire separate specification for the large case sizes when mounted on the substrate.

7. INDUSTRIAL WASTE DISPOSAL



Dispose this product as industrial waste in accordance with the Industrial Waste Law.

8. PERFORMANCE


table 1

No.	Item	Performance	Test or inspection method																
1	External Appearance	No defects which may affect performance.	Inspect with magnifying glass (3×), in case of C0603 type, with magnifying glass (10×)																
2	Insulation Resistance	10,000MΩ or 500MΩ·μF min. (As for the capacitors of rated voltage 16, 10, 6.3V DC and the item below, 10,000 MΩ or 100MΩ·μF min.,) whichever smaller. C1005X5R1E683 C1005X5R1E104 C1608X5R1E334 C1608X5R1E474 C1608X5R1E684 C1608X5R1E105 C2012X5R1E335 C2012X5R1E475	Apply rated voltage for 60s. As for the rated voltage 630V DC, apply 500V.																
3	Voltage Proof	Withstand test voltage without insulation breakdown or other damage.	<table border="1"> <thead> <tr> <th>Class</th><th>Rated voltage</th><th>Apply voltage</th></tr> </thead> <tbody> <tr> <td rowspan="2">Class1</td><td>100V and under</td><td>3 × rated voltage</td></tr> <tr> <td>Over 100V</td><td>1.5 × rated voltage</td></tr> <tr> <td rowspan="2">Class2</td><td>100V and under</td><td>2.5 × rated voltage</td></tr> <tr> <td>Over 100V</td><td>1.5 × rated voltage</td></tr> </tbody> </table> <p>Above DC voltage shall be applied for 1 to 5s. Charge / discharge current shall not exceed 50mA.</p>	Class	Rated voltage	Apply voltage	Class1	100V and under	3 × rated voltage	Over 100V	1.5 × rated voltage	Class2	100V and under	2.5 × rated voltage	Over 100V	1.5 × rated voltage			
Class	Rated voltage	Apply voltage																	
Class1	100V and under	3 × rated voltage																	
	Over 100V	1.5 × rated voltage																	
Class2	100V and under	2.5 × rated voltage																	
	Over 100V	1.5 × rated voltage																	
4	Capacitance	Within the specified tolerance.	<table border="1"> <thead> <tr> <th>Class</th><th>Capacitance</th><th>Measuring frequency</th><th>Measuring voltage</th></tr> </thead> <tbody> <tr> <td rowspan="2">Class1</td><td>1000pF and under</td><td>1MHz±10%</td><td rowspan="2">0.5~5Vrms</td></tr> <tr> <td>Over 1000pF</td><td>1kHz±10%</td></tr> <tr> <td rowspan="2">Class2</td><td>10uF and under</td><td>1kHz±10%</td><td rowspan="2">1.0±0.2Vrms</td></tr> <tr> <td>Over 10uF</td><td>120Hz±20%</td></tr> </tbody> </table> <p>The measurement voltage of items below, 0.5±0.2Vrms. C1005X5R0J155 C1005X5R0J225</p>	Class	Capacitance	Measuring frequency	Measuring voltage	Class1	1000pF and under	1MHz±10%	0.5~5Vrms	Over 1000pF	1kHz±10%	Class2	10uF and under	1kHz±10%	1.0±0.2Vrms	Over 10uF	120Hz±20%
Class	Capacitance	Measuring frequency	Measuring voltage																
Class1	1000pF and under	1MHz±10%	0.5~5Vrms																
	Over 1000pF	1kHz±10%																	
Class2	10uF and under	1kHz±10%	1.0±0.2Vrms																
	Over 10uF	120Hz±20%																	
5	Q (Class1) Dissipation Factor (Class2)	Please refer to the table A in the end of the specification	See No.4 in this table for measuring condition.																

(continued)

No.	Item	Performance	Test or inspection method															
6	Temperature Characteristics of Capacitance (Class1)	<table border="1"> <tr> <td>T.C.</td><td>Temperature Coefficient</td></tr> <tr> <td>C0G</td><td>0 ± 30 (ppm/$^{\circ}$C)</td></tr> </table> Capacitance drift within $\pm 0.2\%$ or $\pm 0.05\text{pF}$, whichever larger.	T.C.	Temperature Coefficient	C0G	0 ± 30 (ppm/ $^{\circ}$ C)	Temperature coefficient shall be calculated based on values at 25°C and 85°C temperature. Measuring temperature below 20°C shall be -10°C and -25°C .											
T.C.	Temperature Coefficient																	
C0G	0 ± 30 (ppm/ $^{\circ}$ C)																	
7	Temperature Characteristics of Capacitance (Class2)	<table border="1"> <tr> <td>Capacitance Change (%)</td></tr> <tr> <td>No voltage applied</td></tr> <tr> <td>X5R : ± 15</td></tr> <tr> <td>X7R : ± 15</td></tr> <tr> <td>Y5V : + 22/-82</td></tr> </table>	Capacitance Change (%)	No voltage applied	X5R : ± 15	X7R : ± 15	Y5V : + 22/-82	Capacitance shall be measured by the steps shown in the following table after thermal equilibrium is obtained for each step. ΔC be calculated ref. STEP3 reading <table border="1"> <thead> <tr> <th>Step</th><th>Temperature($^{\circ}$C)</th></tr> </thead> <tbody> <tr> <td>1</td><td>Reference temp. ± 2</td></tr> <tr> <td>2</td><td>Min. operating temp. ± 3</td></tr> <tr> <td>3</td><td>Reference temp. ± 2</td></tr> <tr> <td>4</td><td>Max. operating temp. ± 2</td></tr> </tbody> </table> <p>As for measuring voltage, please refer to the table A in the end of the specification. As for Min. / Max. operating temp. and Reference temp., please refer to " 4. operating temperature range " at page 3.</p>	Step	Temperature($^{\circ}$ C)	1	Reference temp. ± 2	2	Min. operating temp. ± 3	3	Reference temp. ± 2	4	Max. operating temp. ± 2
Capacitance Change (%)																		
No voltage applied																		
X5R : ± 15																		
X7R : ± 15																		
Y5V : + 22/-82																		
Step	Temperature($^{\circ}$ C)																	
1	Reference temp. ± 2																	
2	Min. operating temp. ± 3																	
3	Reference temp. ± 2																	
4	Max. operating temp. ± 2																	
8	Robustness of Terminations	No sign of termination coming off, breakage of ceramic, or other abnormal signs.	Reflow solder the capacitors on a P.C.Board shown in Appendix 1a or Appendix 1b and apply a pushing force of 2N (C0603 and C1005) or 5N (C1608, C2012, C3216, C3225, C4532, C5750) with $10 \pm 1\text{s}$. 															
9	Bending	No mechanical damage.	Reflow solder the capacitors on a P.C.Board shown in Appendix 2a or Appendix 2b and bend it for 1mm. 															

(continued)

No.	Item	Performance	Test or inspection method																																		
10	Solderability	<p>New solder to cover over 75% of termination. 25% may have pin holes or rough spots but not concentrated in one spot. Ceramic surface of A sections shall not be exposed due to melting or shifting of termination material.</p> 	<p>Completely soak both terminations in solder at $235\pm5^{\circ}\text{C}$ for $2\pm0.5\text{s}$.</p> <p>Solder : H63A (JIS Z 3282)</p> <p>Flux : Isopropyl alcohol (JIS K 8839) Rosin(JIS K 5902) 25% solid solution.</p>																																		
11	Resistance to solder heat	<table border="1"> <tr> <td>External appearance</td> <td colspan="2">No cracks are allowed and terminations shall be covered at least 60% with new solder.</td> </tr> <tr> <td>Capacitance</td> <td colspan="2"> <table border="1"> <tr> <td>Characteristics</td> <td>Change from the value before test</td> </tr> <tr> <td>Class1</td> <td>C0G</td> <td>Capacitance drift within $\pm 2.5\%$ or $\pm 0.25\text{pF}$, whichever larger.</td> </tr> <tr> <td>Class2</td> <td>X5R X7R Y5V</td> <td>$\pm 7.5\%$ $\pm 7.5\%$ $\pm 20\%$</td> </tr> </table> </td> </tr> <tr> <td>Q (Class1)</td> <td colspan="2"> <table border="1"> <tr> <td>Capacitance</td> <td>Q</td> </tr> <tr> <td>30pF and over</td> <td>1,000 min.</td> </tr> <tr> <td>Under 30pF</td> <td>400+20×C min.</td> </tr> <tr> <td colspan="2">C : Rated capacitance (pF)</td> </tr> </table> </td> </tr> <tr> <td>D.F. (Class2)</td> <td colspan="2">Meet the initial spec.</td> </tr> <tr> <td>Insulation Resistance</td> <td colspan="2">Meet the initial spec.</td> </tr> <tr> <td>Voltage proof</td> <td colspan="2">No insulation breakdown or other damage.</td> </tr> </table>	External appearance	No cracks are allowed and terminations shall be covered at least 60% with new solder.		Capacitance	<table border="1"> <tr> <td>Characteristics</td> <td>Change from the value before test</td> </tr> <tr> <td>Class1</td> <td>C0G</td> <td>Capacitance drift within $\pm 2.5\%$ or $\pm 0.25\text{pF}$, whichever larger.</td> </tr> <tr> <td>Class2</td> <td>X5R X7R Y5V</td> <td>$\pm 7.5\%$ $\pm 7.5\%$ $\pm 20\%$</td> </tr> </table>		Characteristics	Change from the value before test	Class1	C0G	Capacitance drift within $\pm 2.5\%$ or $\pm 0.25\text{pF}$, whichever larger.	Class2	X5R X7R Y5V	$\pm 7.5\%$ $\pm 7.5\%$ $\pm 20\%$	Q (Class1)	<table border="1"> <tr> <td>Capacitance</td> <td>Q</td> </tr> <tr> <td>30pF and over</td> <td>1,000 min.</td> </tr> <tr> <td>Under 30pF</td> <td>400+20×C min.</td> </tr> <tr> <td colspan="2">C : Rated capacitance (pF)</td> </tr> </table>		Capacitance	Q	30pF and over	1,000 min.	Under 30pF	400+20×C min.	C : Rated capacitance (pF)		D.F. (Class2)	Meet the initial spec.		Insulation Resistance	Meet the initial spec.		Voltage proof	No insulation breakdown or other damage.		<p>Completely soak both terminations in solder at $260\pm5^{\circ}\text{C}$ for $5\pm1\text{s}$.</p> <p>Preheating condition Temp. : $150\pm10^{\circ}\text{C}$ Time : 1 to 2min.</p> <p>Flux : Isopropyl alcohol (JIS K 8839) Rosin (JIS K 5902) 25% solid solution.</p> <p>Solder : H63A (JIS Z 3282)</p> <p>Leave the capacitors in ambient condition for 6 to 24h (Class1) or $24\pm2\text{h}$ (Class2) before measurement.</p>
External appearance	No cracks are allowed and terminations shall be covered at least 60% with new solder.																																				
Capacitance	<table border="1"> <tr> <td>Characteristics</td> <td>Change from the value before test</td> </tr> <tr> <td>Class1</td> <td>C0G</td> <td>Capacitance drift within $\pm 2.5\%$ or $\pm 0.25\text{pF}$, whichever larger.</td> </tr> <tr> <td>Class2</td> <td>X5R X7R Y5V</td> <td>$\pm 7.5\%$ $\pm 7.5\%$ $\pm 20\%$</td> </tr> </table>		Characteristics	Change from the value before test	Class1	C0G	Capacitance drift within $\pm 2.5\%$ or $\pm 0.25\text{pF}$, whichever larger.	Class2	X5R X7R Y5V	$\pm 7.5\%$ $\pm 7.5\%$ $\pm 20\%$																											
Characteristics	Change from the value before test																																				
Class1	C0G	Capacitance drift within $\pm 2.5\%$ or $\pm 0.25\text{pF}$, whichever larger.																																			
Class2	X5R X7R Y5V	$\pm 7.5\%$ $\pm 7.5\%$ $\pm 20\%$																																			
Q (Class1)	<table border="1"> <tr> <td>Capacitance</td> <td>Q</td> </tr> <tr> <td>30pF and over</td> <td>1,000 min.</td> </tr> <tr> <td>Under 30pF</td> <td>400+20×C min.</td> </tr> <tr> <td colspan="2">C : Rated capacitance (pF)</td> </tr> </table>		Capacitance	Q	30pF and over	1,000 min.	Under 30pF	400+20×C min.	C : Rated capacitance (pF)																												
Capacitance	Q																																				
30pF and over	1,000 min.																																				
Under 30pF	400+20×C min.																																				
C : Rated capacitance (pF)																																					
D.F. (Class2)	Meet the initial spec.																																				
Insulation Resistance	Meet the initial spec.																																				
Voltage proof	No insulation breakdown or other damage.																																				

(continued)

No.	Item		Performance		Test or inspection method							
12	Vibration	External appearance	No mechanical damage.		Reflow solder the capacitors on a P.C.Board shown in Appendix 1a or Appendix 1b before testing. Vibrate the capacitors with amplitude of 1.5mm P-P changing the frequencies from 10Hz to 55Hz and back to 10Hz in about 1min. Repeat this for 2h each in 3 perpendicular directions.							
		Capacitance	<table border="1"> <thead> <tr> <th colspan="2">Characteristics</th> <th>Change from the value before test</th> </tr> </thead> <tbody> <tr> <td>Class1</td> <td>C0G</td> <td>Capacitance drift within $\pm 2.5\%$ or $\pm 0.25\text{pF}$, whichever larger.</td> </tr> <tr> <td>Class2</td> <td>X5R X7R Y5V</td> <td>$\pm 7.5\%$ $\pm 7.5\%$ $\pm 20\%$</td> </tr> </tbody> </table>			Characteristics		Change from the value before test	Class1	C0G	Capacitance drift within $\pm 2.5\%$ or $\pm 0.25\text{pF}$, whichever larger.	Class2
Characteristics		Change from the value before test										
Class1	C0G	Capacitance drift within $\pm 2.5\%$ or $\pm 0.25\text{pF}$, whichever larger.										
Class2	X5R X7R Y5V	$\pm 7.5\%$ $\pm 7.5\%$ $\pm 20\%$										
Q (Class1)	<table border="1"> <thead> <tr> <th>Capacitance</th> <th>Q</th> </tr> </thead> <tbody> <tr> <td>30pF and over</td> <td>1,000 min.</td> </tr> <tr> <td>Under 30pF</td> <td>400+20×C min.</td> </tr> </tbody> </table>			Capacitance	Q	30pF and over	1,000 min.	Under 30pF	400+20×C min.			
Capacitance	Q											
30pF and over	1,000 min.											
Under 30pF	400+20×C min.											
D.F. (Class2)	Meet the initial spec.											
13	Temperature cycle	External appearance	No mechanical damage.		Reflow solder the capacitors on a P.C.Board shown in Appendix 1a or Appendix 1b before testing. Expose the capacitors in the condition step1 through step 4 and repeat 5 times consecutively. Leave the capacitors in ambient condition for 6 to 24h (Class 1) or 24±2h (Class 2) before measurement.							
		Capacitance	<table border="1"> <thead> <tr> <th colspan="2">Characteristics</th> <th>Change from the value before test</th> </tr> </thead> <tbody> <tr> <td>Class1</td> <td>C0G</td> <td>Please refer to the table A in the end of the specification.</td> </tr> <tr> <td>Class2</td> <td>X5R X7R Y5V</td> <td></td> </tr> </tbody> </table>			Characteristics		Change from the value before test	Class1	C0G	Please refer to the table A in the end of the specification.	Class2
Characteristics		Change from the value before test										
Class1	C0G	Please refer to the table A in the end of the specification.										
Class2	X5R X7R Y5V											
Q (Class1)	<table border="1"> <thead> <tr> <th>Capacitance</th> <th>Q</th> </tr> </thead> <tbody> <tr> <td>30pF and over</td> <td>1,000 min.</td> </tr> <tr> <td>Under 30pF</td> <td>400+20×C min.</td> </tr> </tbody> </table>			Capacitance	Q	30pF and over	1,000 min.	Under 30pF	400+20×C min.			
Capacitance	Q											
30pF and over	1,000 min.											
Under 30pF	400+20×C min.											
C : Rated capacitance (pF)												
D.F. (Class2)	Meet the initial spec.											
Insulation Resistance	Meet the initial spec.											
Voltage proof	No insulation breakdown or other damage.											

(continued)

No.	Item		Performance		Test or inspection method													
14	Moisture Resistance (Steady State)	External appearance	No mechanical damage.		Reflow solder the capacitors on a P.C.Board shown in Appendix 1a or Appendix 1b before testing. Leave at temperature $40\pm2^{\circ}\text{C}$, 90 to 95%RH for 500 +24,0h.													
		Capacitance	<table border="1"> <thead> <tr> <th colspan="2">Characteristics</th> <th>Change from the value before test</th> </tr> <tr> <th>Class1</th> <th>C0G</th> <td>Please refer to the table A in the end of the specification.</td> </tr> </thead> <tbody> <tr> <td></td> <td>X5R</td> <td></td> </tr> <tr> <td>Class2</td> <td>X7R</td> <td></td> </tr> <tr> <td></td> <td>Y5V</td> <td></td> </tr> </tbody> </table>			Characteristics		Change from the value before test	Class1	C0G	Please refer to the table A in the end of the specification.		X5R		Class2	X7R		
Characteristics		Change from the value before test																
Class1	C0G	Please refer to the table A in the end of the specification.																
	X5R																	
Class2	X7R																	
	Y5V																	
Q (Class1)	<table border="1"> <thead> <tr> <th>Capacitance</th> <th>Q</th> </tr> </thead> <tbody> <tr> <td>30pF and over</td> <td>350 and over</td> </tr> <tr> <td>10pF and over to under 30pF</td> <td>$275+5/2\times C \text{ min.}$</td> </tr> <tr> <td>Under 10pF</td> <td>$200+10\times C \text{ min.}$</td> </tr> </tbody> </table> <p>C : Rated capacitance (pF)</p>		Capacitance	Q	30pF and over	350 and over	10pF and over to under 30pF	$275+5/2\times C \text{ min.}$	Under 10pF	$200+10\times C \text{ min.}$	Leave the capacitors in ambient condition for 6 to 24h (Class1) or $24\pm2\text{h}$ (Class2) before measurement.							
Capacitance	Q																	
30pF and over	350 and over																	
10pF and over to under 30pF	$275+5/2\times C \text{ min.}$																	
Under 10pF	$200+10\times C \text{ min.}$																	
D.F. (Class2)	<p>Characteristics X5R : 200% of initial spec. max. X7R : 200% of initial spec. max. Y5V : 150% of initial spec. max.</p>																	
Insulation Resistance	<p>1,000MΩ or $50\text{M}\Omega\cdot\mu\text{F}$ min. (As for the capacitors of rated voltage 16, 10, 6.3V DC and item below, 1,000MΩ or $10\text{M}\Omega\cdot\mu\text{F}$ min.,) whichever smaller.</p> <p>C1005X5R1E683 C1005X5R1E104 C1608X5R1E334 C1608X5R1E474 C1608X5R1E684 C1608X5R1E105 C2012X5R1E335 C2012X5R1E475</p>																	

(continued)

No.	Item		Performance		Test or inspection method								
15	Moisture Resistance	External appearance	No mechanical damage.		Reflow solder the capacitors on a P.C.Board shown in Appendix 1a or Appendix 1b before testing.								
		Capacitance	<table border="1"> <thead> <tr> <th colspan="2">Characteristics</th> <th>Change from the value before test</th> </tr> <tr> <th>Class1</th> <th>C0G</th> <td rowspan="3">Please refer to the table A in the end of the specification.</td> </tr> </thead> <tbody> <tr> <td>X5R</td> <td>X7R</td> </tr> <tr> <td>Class2</td> <td>Y5V</td> </tr> </tbody> </table>			Characteristics		Change from the value before test	Class1	C0G	Please refer to the table A in the end of the specification.	X5R	X7R
Characteristics		Change from the value before test											
Class1	C0G	Please refer to the table A in the end of the specification.											
X5R	X7R												
Class2	Y5V												
Q (Class1)	Capacitance	Q	Apply the rated voltage at temperature $40\pm2^{\circ}\text{C}$ and 90 to 95%RH for 500 +24,0h. Charge/discharge current shall not exceed 50mA.										
	30pF and over	200 and over											
	Under 30pF	100+10/3×C min.	Leave the capacitors in ambient condition for 6 to 24h (Class1) or 24±2h (Class2) before measurement. Voltage conditioning (only for class 2) Voltage treat the capacitors under testing temperature and voltage for 1 hour. Leave the capacitors in ambient condition for 24±2h before measurement. Use this measurement for initial value.										
D.F. (Class2)	Characteristics X5R : 200% of initial spec. max. X7R : 200% of initial spec. max. Y5V : 150% of initial spec. max.												
Insulation Resistance	500MΩ or 25MΩ·μF min. (As for the capacitors of rated voltage 16, 10, 6.3V DC and item below, 500MΩ or 5MΩ·μF min.,) whichever smaller. C1005X5R1E683 C1005X5R1E104 C1608X5R1E334 C1608X5R1E474 C1608X5R1E684 C1608X5R1E105 C2012X5R1E335 C2012X5R1E475												

(continued)


No.	Item	Performance		Test or inspection method							
16	Life	External appearance	No mechanical damage.								
		Capacitance	<table border="1"> <thead> <tr> <th colspan="2">Characteristics</th> <th>Change from the value before test</th> </tr> </thead> <tbody> <tr> <td>Class1</td><td>C0G</td><td>Please refer to the table A in the end of the specification.</td></tr> <tr> <td>Class2</td><td>X5R X7R Y5V</td><td></td></tr> </tbody> </table>		Characteristics		Change from the value before test	Class1	C0G	Please refer to the table A in the end of the specification.	Class2
Characteristics		Change from the value before test									
Class1	C0G	Please refer to the table A in the end of the specification.									
Class2	X5R X7R Y5V										
Q (Class1)	<table border="1"> <thead> <tr> <th>Capacitance</th> <th>Q</th> </tr> </thead> <tbody> <tr> <td>30pF and over</td><td>350 and over</td></tr> <tr> <td>10pF and over to under 30pF</td><td>275+5/2×C min.</td></tr> <tr> <td>Under 10pF</td><td>200+10×C min.</td></tr> </tbody> </table>		Capacitance	Q	30pF and over	350 and over	10pF and over to under 30pF	275+5/2×C min.	Under 10pF	200+10×C min.	Test condition : maximum operating temperature $\pm 2^{\circ}\text{C}$ for 1,000 +48,0h As for applied voltage, please refer to the table A in the end of the specification. Charge/discharge current shall not exceed 50mA.
Capacitance	Q										
30pF and over	350 and over										
10pF and over to under 30pF	275+5/2×C min.										
Under 10pF	200+10×C min.										
<p>C : Rated capacitance (pF)</p> <p>D.F. (Class2)</p> <p>Characteristics X5R : 200% of initial spec. max. X7R : 200% of initial spec. max. Y5V : 150% of initial spec. max.</p>		Leave the capacitors in ambient condition for 6 to 24h (Class1) or 24±2h (Class2) before measurement.									
<p>Insulation Resistance</p> <p>1,000MΩ or 50MΩ·μF min. (As for the capacitors of rated voltage 16, 10, 6.3V DC and the item below, 1,000 MΩ or 10MΩ·μF min.,) whichever smaller.</p> <p>C1005X5R1E683 C1005X5R1E104 C1608X5R1E334 C1608X5R1E474 C1608X5R1E684 C1608X5R1E105 C2012X5R1E335 C2012X5R1E475</p>		Voltage conditioning Voltage treat the capacitors under testing temperature and voltage for 1 hour. Leave the capacitors in ambient condition for 24±2h before measurement. Use this measurement for initial value.									

*As for the initial measurement of capacitors (Class2) on number 7,11,12,13 and 14, leave capacitors at 150 –10,0°C for 1 hour and measure the value after leaving capacitors for 24±2h in ambient condition.

Appendix - 1a

P.C. Board for reliability test


Applied for C0603, C1005, C1608, C2012, C3216



Appendix - 1b

P.C. Board for reliability test


Applied for C3225, C4532, C5750



Appendix - 2a

P.C. Board for bending test


Applied for C0603, C1005



Appendix - 2b

P.C. Board for bending test

Applied for C1608, C2012, C3216, C3225, C4532, C5750



Material : Glass Epoxy (As per JIS C6484 GE4)

P.C. Board thickness : Appendix-2a 0.8mm


Appendix-1a, 1b, 2b 1.6mm

Copper (thickness 0.035mm)

Solder resist

TDK (EIA style)	Dimensions (mm)		
	a	b	c
C0603 (CC0201)	0.3	0.8	0.3
C1005 (CC0402)	0.4	1.5	0.5
C1608 (CC0603)	1.0	3.0	1.2
C2012 (CC0805)	1.2	4.0	1.65
C3216 (CC1206)	2.2	5.0	2.0
C3225 (CC1210)	2.2	5.0	2.9
C4532 (CC1812)	3.5	7.0	3.7
C5750 (CC2220)	4.5	8.0	5.6

9. INSIDE STRUCTURE AND MATERIAL



No.	NAME	MATERIAL	
		Class1	Class2
1	Dielectric	CaZrO ₃	BaTiO ₃
2	Electrode	Nickel (Ni)	
3	Termination	Copper (Cu)	
4		Nickel (Ni)	
5		Tin (Sn)	


10. RECOMMENDATION


As for C3225, C4532 and C5750 types, It is recommended to provide a slit (about 1mm wide) in the board under the components to improve washing Flux. And please make sure to dry detergent up completely before.

11. SOLDERING CONDITION

As for C0603, C1005, C3225, C4532 and C5750 types, reflow soldering only.














12. Caution

No.	Process	Condition
1	Operating Condition (Storage, Transportation)	<p>1-1. Storage</p> <p>1) The capacitors must be stored in an ambient temperature of 5 to 40°C with a relative humidity of 20 to 70%RH. The products should be used within 6 months upon receipt.</p> <p>2) The capacitors must be operated and stored in an environment free of dew condensation and these gases such as Hydrogen Sulphide, Hydrogen Sulphate, Chlorine, Ammonia and sulfur.</p> <p>3) Avoid storing in sun light and falling of dew.</p> <p>4) Do not use capacitors under high humidity and high and low atmospheric pressure which may affect capacitors reliability.</p> <p>5) Capacitors should be tested for the solderability when they are stored for long time.</p> <p>1-2. Handling in transportation</p> <p>In case of the transportation of the capacitors, the performance of the capacitors may be deteriorated depending on the transportation condition. (Refer to JEITA RCR-2335B 9.2 Handling in transportation)</p>
2	Circuit design 	<p>2-1. Operating temperature</p> <p>Operating temperature should be followed strictly within this specification, especially be careful with maximum temperature.</p> <p>1) Do not use capacitors above the maximum allowable operating temperature.</p> <p>2) Surface temperature including self heating should be below maximum operating temperature. (Due to dielectric loss, capacitors will heat itself when AC is applied. Especially at high frequencies around its SRF, the heat might be so extreme that it may damage itself or the product mounted on. Please design the circuit so that the maximum temperature of the capacitors including the self heating to be below the maximum allowable operating temperature. Temperature rise at capacitor surface shall be below 20°C)</p> <p>3) The electrical characteristics of the capacitors will vary depending on the temperature. The capacitors should be selected and designed in taking the temperature into consideration.</p> <p>2-2. Operating voltage</p> <p>1) Operating voltage across the terminals should be below the rated voltage. When AC and DC are super imposed, V_{0-P} must be below the rated voltage. ____ (1) and (2) AC or pulse with overshooting, V_{P-P} must be below the rated voltage. ____ (3), (4) and (5) When the voltage is started to apply to the circuit or it is stopped applying, the irregular voltage may be generated for a transit period because of resonance or switching. Be sure to use the capacitors within rated voltage containing these Irregular voltage.</p> 

No.	Process	Condition																																																													
2	Circuit design ⚠ Caution	<p>2) Even below the rated voltage, if repetitive high frequency AC or pulse is applied, the reliability of the capacitors may be reduced.</p> <p>3) The effective capacitance will vary depending on applied DC and AC voltages. The capacitors should be selected and designed in taking the voltages into consideration.</p> <p>2-3. Frequency When the capacitors (Class 2) are used in AC and/or pulse voltages, the capacitors may vibrate themselves and generate audible sound.</p>																																																													
3	Designing P.C.board	<p>The amount of solder at the terminations has a direct effect on the reliability of the capacitors.</p> <p>1) The greater the amount of solder, the higher the stress on the chip capacitors, and the more likely that it will break. When designing a P.C.board, determine the shape and size of the solder lands to have proper amount of solder on the terminations.</p> <p>2) Avoid using common solder land for multiple terminations and provide individual solder land for each terminations.</p> <p>3) Size and recommended land dimensions.</p>  <table border="1" style="margin-left: auto; margin-right: auto;"> <thead> <tr> <th>Type Symbol \</th><th>C1608 (CC0603)</th><th>C2012 (CC0805)</th><th>C3216 (CC1206)</th></tr> </thead> <tbody> <tr> <td>A</td><td>0.7 - 1.0</td><td>1.0 - 1.3</td><td>2.1 - 2.5</td></tr> <tr> <td>B</td><td>0.8 - 1.0</td><td>1.0 - 1.2</td><td>1.1 - 1.3</td></tr> <tr> <td>C</td><td>0.6 - 0.8</td><td>0.8 - 1.1</td><td>1.0 - 1.3</td></tr> </tbody> </table> <table border="1" style="margin-left: auto; margin-right: auto;"> <thead> <tr> <th colspan="5">Reflow soldering (mm)</th></tr> <tr> <th>Type Symbol \</th><th>C0603 (CC0201)</th><th>C1005 (CC0402)</th><th>C1608 (CC0603)</th><th>C2012 (CC0805)</th></tr> </thead> <tbody> <tr> <td>A</td><td>0.25 - 0.35</td><td>0.3 - 0.5</td><td>0.6 - 0.8</td><td>0.9 - 1.2</td></tr> <tr> <td>B</td><td>0.2 - 0.3</td><td>0.35 - 0.45</td><td>0.6 - 0.8</td><td>0.7 - 0.9</td></tr> <tr> <td>C</td><td>0.25 - 0.35</td><td>0.4 - 0.6</td><td>0.6 - 0.8</td><td>0.9 - 1.2</td></tr> </tbody> </table> <table border="1" style="margin-left: auto; margin-right: auto;"> <thead> <tr> <th>Type Symbol \</th><th>C3216 (CC1206)</th><th>C3225 (CC1210)</th><th>C4532 (CC1812)</th><th>C5750 (CC2220)</th></tr> </thead> <tbody> <tr> <td>A</td><td>2.0 - 2.4</td><td>2.0 - 2.4</td><td>3.1 - 3.7</td><td>4.1 - 4.8</td></tr> <tr> <td>B</td><td>1.0 - 1.2</td><td>1.0 - 1.2</td><td>1.2 - 1.4</td><td>1.2 - 1.4</td></tr> <tr> <td>C</td><td>1.1 - 1.6</td><td>1.9 - 2.5</td><td>2.4 - 3.2</td><td>4.0 - 5.0</td></tr> </tbody> </table>	Type Symbol \	C1608 (CC0603)	C2012 (CC0805)	C3216 (CC1206)	A	0.7 - 1.0	1.0 - 1.3	2.1 - 2.5	B	0.8 - 1.0	1.0 - 1.2	1.1 - 1.3	C	0.6 - 0.8	0.8 - 1.1	1.0 - 1.3	Reflow soldering (mm)					Type Symbol \	C0603 (CC0201)	C1005 (CC0402)	C1608 (CC0603)	C2012 (CC0805)	A	0.25 - 0.35	0.3 - 0.5	0.6 - 0.8	0.9 - 1.2	B	0.2 - 0.3	0.35 - 0.45	0.6 - 0.8	0.7 - 0.9	C	0.25 - 0.35	0.4 - 0.6	0.6 - 0.8	0.9 - 1.2	Type Symbol \	C3216 (CC1206)	C3225 (CC1210)	C4532 (CC1812)	C5750 (CC2220)	A	2.0 - 2.4	2.0 - 2.4	3.1 - 3.7	4.1 - 4.8	B	1.0 - 1.2	1.0 - 1.2	1.2 - 1.4	1.2 - 1.4	C	1.1 - 1.6	1.9 - 2.5	2.4 - 3.2	4.0 - 5.0
Type Symbol \	C1608 (CC0603)	C2012 (CC0805)	C3216 (CC1206)																																																												
A	0.7 - 1.0	1.0 - 1.3	2.1 - 2.5																																																												
B	0.8 - 1.0	1.0 - 1.2	1.1 - 1.3																																																												
C	0.6 - 0.8	0.8 - 1.1	1.0 - 1.3																																																												
Reflow soldering (mm)																																																															
Type Symbol \	C0603 (CC0201)	C1005 (CC0402)	C1608 (CC0603)	C2012 (CC0805)																																																											
A	0.25 - 0.35	0.3 - 0.5	0.6 - 0.8	0.9 - 1.2																																																											
B	0.2 - 0.3	0.35 - 0.45	0.6 - 0.8	0.7 - 0.9																																																											
C	0.25 - 0.35	0.4 - 0.6	0.6 - 0.8	0.9 - 1.2																																																											
Type Symbol \	C3216 (CC1206)	C3225 (CC1210)	C4532 (CC1812)	C5750 (CC2220)																																																											
A	2.0 - 2.4	2.0 - 2.4	3.1 - 3.7	4.1 - 4.8																																																											
B	1.0 - 1.2	1.0 - 1.2	1.2 - 1.4	1.2 - 1.4																																																											
C	1.1 - 1.6	1.9 - 2.5	2.4 - 3.2	4.0 - 5.0																																																											

No.	Process	Condition	
3	Designing P.C.board	4) Recommended chip capacitors layout is as following.	
		Disadvantage against bending stress	Advantage against bending stress
	Mounting face	<p style="text-align: center;">Perforation or slit</p> <p>Break P.C.board with mounted side up.</p>	<p style="text-align: center;">Perforation or slit</p> <p>Break P.C.board with mounted side down.</p>
	Chip arrangement (Direction)	<p style="text-align: center;">Mount perpendicularly to perforation or slit</p> <p style="text-align: center;">Perforation or slit</p>	<p style="text-align: center;">Mount in parallel with perforation or slit</p> <p style="text-align: center;">Perforation or slit</p>
	Distance from slit	<p>Closer to slit is higher stress</p> <p style="text-align: center;">l_1</p> <p style="text-align: center;">$(l_1 < l_2)$</p>	<p>Away from slit is less stress</p> <p style="text-align: center;">l_2</p> <p style="text-align: center;">$(l_1 < l_2)$</p>








No.	Process	Condition			
3	Designing P.C.board	<p>5) Mechanical stress varies according to location of chip capacitors on the P.C.board.</p>			
		The stress in capacitors is in the following order. A > B = C > D > E			
	6) Layout recommendation	Example	Use of common solder land	Soldering with chassis	Use of common solder land with other SMD
	Need to avoid				
	Recommendation			$l^2 > l^1$	



No.	Process	Condition															
4	Mounting	<p>4-1. Stress from mounting head If the mounting head is adjusted too low, it may induce excessive stress in the chip capacitors to result in cracking. Please take following precautions.</p> <ol style="list-style-type: none"> 1) Adjust the bottom dead center of the mounting head to reach on the P.C.board surface and not press it. 2) Adjust the mounting head pressure to be 1 to 3N of static weight. 3) To minimize the impact energy from mounting head, it is important to provide support from the bottom side of the P.C.board. See following examples. <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th></th><th style="text-align: center;">Not recommended</th><th style="text-align: center;">Recommended</th></tr> </thead> <tbody> <tr> <td style="text-align: center;">Single sided mounting</td><td style="text-align: center;">  <p>Crack</p> </td><td style="text-align: center;">  <p>Support pin</p> </td></tr> <tr> <td style="text-align: center;">Double-sides mounting</td><td style="text-align: center;">  <p>Solder peeling</p> <p>Crack</p> </td><td style="text-align: center;">  <p>Support pin</p> </td></tr> </tbody> </table> <p>When the centering jaw is worn out, it may give mechanical impact on the capacitors to cause crack. Please control the close up dimension of the centering jaw and provide sufficient preventive maintenance and replacement of it.</p> <p>4-2. Amount of adhesive</p>  <p>Example : C2012 (CC0805), C3216 (CC1206)</p> <table border="1" style="margin-left: auto; margin-right: auto;"> <tr> <td style="text-align: center;">a</td><td style="text-align: center;">0.2mm min.</td></tr> <tr> <td style="text-align: center;">b</td><td style="text-align: center;">70 - 100μm</td></tr> <tr> <td style="text-align: center;">c</td><td style="text-align: center;">Do not touch the solder land</td></tr> </table>		Not recommended	Recommended	Single sided mounting	 <p>Crack</p>	 <p>Support pin</p>	Double-sides mounting	 <p>Solder peeling</p> <p>Crack</p>	 <p>Support pin</p>	a	0.2mm min.	b	70 - 100 μ m	c	Do not touch the solder land
	Not recommended	Recommended															
Single sided mounting	 <p>Crack</p>	 <p>Support pin</p>															
Double-sides mounting	 <p>Solder peeling</p> <p>Crack</p>	 <p>Support pin</p>															
a	0.2mm min.																
b	70 - 100 μ m																
c	Do not touch the solder land																

No.	Process	Condition																				
5	Soldering	<p>5-1. Flux selection Although highly-activated flux gives better solderability, substances which increase activity may also degrade the insulation of the chip capacitors. To avoid such degradation, it is recommended following.</p> <ol style="list-style-type: none"> 1) It is recommended to use a mildly activated rosin flux (less than 0.1wt% chlorine). Strong flux is not recommended. 2) Excessive flux must be avoided. Please provide proper amount of flux. 3) When water-soluble flux is used, enough washing is necessary. <p>5-2. Recommended soldering profile by various methods</p> <div style="display: flex; justify-content: space-around;"> <div style="text-align: center;"> <p>Wave soldering</p> </div> <div style="text-align: center;"> <p>Reflow soldering</p> </div> </div> <div style="display: flex; justify-content: space-around; margin-top: 10px;"> <div style="text-align: center;"> <p>Manual soldering (Solder iron)</p> </div> <div style="text-align: center;"> <p>APPLICATION</p> <p>As for C1608 (CC0603), C2012 (CC0805) and C3216 (CC1206), applied to wave soldering and reflow soldering.</p> <p>As for C0603 (CC0201), C1005 (CC0402), C3225 (CC1210), C4532 (CC1812), C5750 (CC2220), applied only to reflow soldering.</p> </div> </div> <p>5-3. Recommended soldering peak temp and peak temp duration</p> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th rowspan="2">Temp./Duration</th> <th colspan="2">Wave soldering</th> <th colspan="2">Reflow soldering</th> </tr> <tr> <th>Solder</th> <th>Peak temp(°C)</th> <th>Duration(sec.)</th> <th>Peak temp(°C)</th> <th>Duration(sec.)</th> </tr> </thead> <tbody> <tr> <td>Pb-Sn Solder</td> <td>250 max.</td> <td>3 max.</td> <td>230 max.</td> <td>20 max.</td> </tr> <tr> <td>Lead Free Solder</td> <td>260 max.</td> <td>5 max.</td> <td>260 max.</td> <td>10 max.</td> </tr> </tbody> </table> <p>Recommended solder compositions</p> <ul style="list-style-type: none"> Sn-37Pb (Pb-Sn solder) Sn-3.0Ag-0.5Cu (Lead Free Solder) 	Temp./Duration	Wave soldering		Reflow soldering		Solder	Peak temp(°C)	Duration(sec.)	Peak temp(°C)	Duration(sec.)	Pb-Sn Solder	250 max.	3 max.	230 max.	20 max.	Lead Free Solder	260 max.	5 max.	260 max.	10 max.
Temp./Duration	Wave soldering			Reflow soldering																		
	Solder	Peak temp(°C)	Duration(sec.)	Peak temp(°C)	Duration(sec.)																	
Pb-Sn Solder	250 max.	3 max.	230 max.	20 max.																		
Lead Free Solder	260 max.	5 max.	260 max.	10 max.																		

No.	Process	Condition																										
5	Soldering	<p>5-4. Avoiding thermal shock</p> <p>1) Preheating condition</p> <table border="1"> <thead> <tr> <th>Soldering</th><th>Type</th><th>Temp. (°C)</th></tr> </thead> <tbody> <tr> <td>Wave soldering</td><td>C1608(CC0603), C2012(CC0805), C3216(CC1206)</td><td>$\Delta T \leq 150$</td></tr> <tr> <td>Reflow soldering</td><td>C0603(CC0201), C1005(CC0402), C1608(CC0603), C2012(CC0805), C3216(CC1206)</td><td>$\Delta T \leq 150$</td></tr> <tr> <td></td><td>C3225(CC1210), C4532(CC1812), C5750(CC2220)</td><td>$\Delta T \leq 130$</td></tr> <tr> <td>Manual soldering</td><td>C0603(CC0201), C1005(CC0402), C1608(CC0603), C2012(CC0805), C3216(CC1206)</td><td>$\Delta T \leq 150$</td></tr> <tr> <td></td><td>C3225(CC1210), C4532(CC1812), C5750(CC2220)</td><td>$\Delta T \leq 130$</td></tr> </tbody> </table> <p>2) Cooling condition</p> <p>Natural cooling using air is recommended. If the chips are dipped into a solvent for cleaning, the temperature difference (ΔT) must be less than 100°C.</p> <p>5-5. Amount of solder</p> <p>Excessive solder will induce higher tensile force in chip capacitors when temperature changes and it may result in chip cracking. Insufficient solder may detach the capacitors from the P.C.board.</p> <p>The diagram illustrates three scenarios of solder application:</p> <ul style="list-style-type: none"> Excessive solder: Shows a capacitor lead with a large amount of solder applied, resulting in a crack in the chip capacitor due to high tensile force. Adequate solder: Shows a capacitor lead with a moderate amount of solder, indicating the maximum and minimum acceptable levels. Insufficient solder: Shows a capacitor lead with a very small amount of solder, leading to low robustness and potential contact failure or detachment from the P.C.board. <p>5-6. Solder repair by solder iron</p> <p>1) Selection of the soldering iron tip</p> <p>Tip temperature of solder iron varies by its type, P.C.board material and solder land size. The higher the tip temperature, the quicker the operation. However, heat shock may cause a crack in the chip capacitors.</p> <p>Please make sure the tip temp. before soldering and keep the peak temp and time in accordance with following recommended condition. (Please preheat the chip capacitors with the condition in 5-4 to avoid the thermal shock.)</p> <p>Recommended solder iron condition (Pb-Sn Solder and Lead Free Solder)</p> <table border="1"> <thead> <tr> <th>Temp. (°C)</th><th>Duration (sec.)</th><th>Wattage (W)</th><th>Shape (mm)</th></tr> </thead> <tbody> <tr> <td>300 max.</td><td>3 max.</td><td>20 max.</td><td>$\varnothing 3.0$ max.</td></tr> </tbody> </table>	Soldering	Type	Temp. (°C)	Wave soldering	C1608(CC0603), C2012(CC0805), C3216(CC1206)	$\Delta T \leq 150$	Reflow soldering	C0603(CC0201), C1005(CC0402), C1608(CC0603), C2012(CC0805), C3216(CC1206)	$\Delta T \leq 150$		C3225(CC1210), C4532(CC1812), C5750(CC2220)	$\Delta T \leq 130$	Manual soldering	C0603(CC0201), C1005(CC0402), C1608(CC0603), C2012(CC0805), C3216(CC1206)	$\Delta T \leq 150$		C3225(CC1210), C4532(CC1812), C5750(CC2220)	$\Delta T \leq 130$	Temp. (°C)	Duration (sec.)	Wattage (W)	Shape (mm)	300 max.	3 max.	20 max.	$\varnothing 3.0$ max.
Soldering	Type	Temp. (°C)																										
Wave soldering	C1608(CC0603), C2012(CC0805), C3216(CC1206)	$\Delta T \leq 150$																										
Reflow soldering	C0603(CC0201), C1005(CC0402), C1608(CC0603), C2012(CC0805), C3216(CC1206)	$\Delta T \leq 150$																										
	C3225(CC1210), C4532(CC1812), C5750(CC2220)	$\Delta T \leq 130$																										
Manual soldering	C0603(CC0201), C1005(CC0402), C1608(CC0603), C2012(CC0805), C3216(CC1206)	$\Delta T \leq 150$																										
	C3225(CC1210), C4532(CC1812), C5750(CC2220)	$\Delta T \leq 130$																										
Temp. (°C)	Duration (sec.)	Wattage (W)	Shape (mm)																									
300 max.	3 max.	20 max.	$\varnothing 3.0$ max.																									

No.	Process	Condition
5	Soldering	<p>2) Direct contact of the soldering iron with ceramic dielectric of chip capacitors may cause crack. Do not touch the ceramic dielectric and the terminations by solder iron.</p> <p>5-7. Sn-Zn solder Sn-Zn solder affects product reliability. Please contact TDK in advance when utilize Sn-Zn solder.</p> <p>5-8. Countermeasure for tombstone The misalignment between the mounted positions of the capacitors and the land patterns should be minimized. The tombstone phenomenon may occur especially the capacitors are mounted (in longitudinal direction) in the same direction of the reflow soldering. (Refer to JEITA RCR-2335B Annex A (Informative) Recommendations to prevent the tombstone phenomenon)</p>
6	Cleaning	<p>1) If an unsuitable cleaning fluid is used, flux residue or some foreign articles may stick to chip capacitors surface to deteriorate especially the insulation resistance.</p> <p>2) If cleaning condition is not suitable, it may damage the chip capacitors.</p> <p>2)-1. Insufficient washing (1) Terminal electrodes may corrode by Halogen in the flux.</p> <p>(2) Halogen in the flux may adhere on the surface of capacitors, and lower the insulation resistance.</p> <p>(3) Water soluble flux has higher tendency to have above mentioned problems (1) and (2).</p> <p>2)-2. Excessive washing When ultrasonic cleaning is used, excessively high ultrasonic energy output can affect the connection between the ceramic chip capacitor's body and the terminal electrode. To avoid this, following is the recommended condition.</p> <p style="padding-left: 40px;">Power : 20 W/ℓ max.</p> <p style="padding-left: 40px;">Frequency : 40 kHz max.</p> <p style="padding-left: 40px;">Washing time : 5 minutes max.</p> <p>2)-3. If the cleaning fluid is contaminated, density of Halogen increases, and it may bring the same result as insufficient cleaning.</p>

No.	Process	Condition						
7	Coating and molding of the P.C.board	<p>1) When the P.C.board is coated, please verify the quality influence on the product.</p> <p>2) Please verify carefully that there is no harmful decomposing or reaction gas emission during curing which may damage the chip capacitors.</p> <p>3) Please verify the curing temperature.</p>						
8	Handling after chip mounted ⚠ Caution	<p>1) Please pay attention not to bend or distort the P.C.board after soldering in handling otherwise the chip capacitors may crack.</p>  <p>2) When functional check of the P.C.board is performed, check pin pressure tends to be adjusted higher for fear of loose contact. But if the pressure is excessive and bend the P.C.board, it may crack the chip capacitors or peel the terminations off. Please adjust the check pins not to bend the P.C.board.</p> <table border="1" data-bbox="522 1098 1403 1436"> <thead> <tr> <th>Item</th><th>Not recommended</th><th>Recommended</th></tr> </thead> <tbody> <tr> <td>Board bending</td><td>  </td><td>  </td></tr> </tbody> </table>	Item	Not recommended	Recommended	Board bending		
Item	Not recommended	Recommended						
Board bending								

No.	Process	Condition
9	Handling of loose chip capacitors	<p>1) If dropped the chip capacitors may crack. Once dropped do not use it. Especially, the large case sized chip capacitors are tendency to have cracks easily, so please handle with care.</p>  <p>Floor</p> <p>2) Piling the P.C.board after mounting for storage or handling, the corner of the P.C. board may hit the chip capacitors of another board to cause crack.</p> 
10	Capacitance aging	The capacitors (Class 2) have aging in the capacitance. They may not be used in precision time constant circuit. In case of the time constant circuit, the evaluation should be done well.
11	Estimated life and estimated failure rate of capacitors	<p>As per the estimated life and the estimated failure rate depend on the temperature and the voltage. This can be calculated by the equation described in JEITA RCR-2335B Annex F(Informative) Calculation of the estimated lifetime and the estimated failure rate (Temperature acceleration : 3rd powered law, Voltage acceleration : 10°C law)</p> <p>The failure rate can be decreased by reducing the temperature and the voltage but they will not be guaranteed.</p>
12	Others ⚠ Caution	<p>The products listed on this specification sheet are intended for use in general electronic equipment (AV equipment, telecommunications equipment, home appliances, amusement equipment, computer equipment, personal equipment, office equipment, measurement equipment, industrial robots) under a normal operation and use condition.</p> <p>The products are not designed or warranted to meet the requirements of the applications listed below, whose performance and/or quality require a more stringent level of safety or reliability, or whose failure, malfunction or trouble could cause serious damage to society, person or property. Please understand that we are not responsible for any damage or liability caused by use of the products in any of the applications below or for any other use exceeding the range or conditions set forth in this specification sheet.</p> <p>Aerospace/Aviation equipment. Transportation equipment (cars, electric trains, ships, etc.) Medical equipment. Power-generation control equipment. Atomic energy-related equipment. Seabed equipment. Transportation control equipment. Public information-processing equipment. Military equipment. Electric heating apparatus, burning equipment. Disaster prevention/crime prevention equipment. Safety equipment. Other applications that are not considered general-purpose applications.</p> <p>When using this product in general-purpose applications, you are kindly requested to take into consideration securing protection circuit/equipment or providing backup circuits, etc., to ensure higher safety.</p>

13. Packaging label

Packaging shall be done to protect the components from the damage during transportation and storing, and a label which has the following information shall be attached.

- 1) Inspection No.
- 2) TDK P/N
- 3) Customer's P/N
- 4) Quantity

*Composition of Inspection No.

Example M 9 A - OO - OOO
(a) (b) (c) (d) (e)

- a) Line code
- b) Last digit of the year
- c) Month and A for January and B for February and so on. (Skip I)
- d) Inspection Date of the month.
- e) Serial No. of the day

14. Bulk packaging quantity

Total number of components in a plastic bag for bulk packaging : 1,000pcs.
As for C0603 and C1005 types, not available for bulk packaging.

15. TAPE PACKAGING SPECIFICATION


1. CONSTRUCTION AND DIMENSION OF TAPING

1-1. Dimensions of carrier tape

Dimensions of paper tape shall be according to Appendix 3, 4, 5.

Dimensions of plastic tape shall be according to Appendix 6, 7.

1-2. Bulk part and leader of taping




1-3. Dimensions of reel

Dimensions of Ø178 reel shall be according to Appendix 8, 9.


Dimensions of Ø330 reel shall be according to Appendix 10, 11.

1-4. Structure of taping


Type 1



Type 2



Type 3




2. CHIP QUANTITY

Please refer to the table A in the end of the specification.

3. PERFORMANCE SPECIFICATIONS

3-1. Fixing peeling strength (top tape)

0.05-0.7N. (See the following figure.)



3-2. Carrier tape shall be flexible enough to be wound around a minimum radius of 30mm with components in tape.


3-3. The missing of components shall be less than 0.1%

3-4. Components shall not stick to fixing tape.

3-5. The fixing tapes shall not protrude beyond the edges of the carrier tape
not shall cover the sprocket holes.

Appendix 3

Paper Tape




<u>Symbol</u> <u>Type</u>	A	B	C	D	E	F
C0603 (CC0201)	(0.38)	(0.68)				
C1005 (CC0402)	(0.65)	(1.15)	8.00 ± 0.30	3.50 ± 0.05	1.75 ± 0.10	2.00 ± 0.05
<u>Symbol</u> <u>Type</u>	G	H	J	k	T	
C0603 (CC0201)	2.00 ± 0.05	4.00 ± 0.05	Ø 1.5 ^{+0.10} ₀	0.35 ± 0.02	0.40 min.	
C1005 (CC0402)				0.55 ± 0.03	0.59 min.	

* The values in the parentheses () are for reference.

Appendix 4

Paper Tape




<u>Symbol</u> <u>Type</u>	A	B	C	D	E	F
C1005 (CC0402)	(0.65)	(1.15)	8.00 ± 0.30	3.50 ± 0.05	1.75 ± 0.10	2.00 ± 0.05
<u>Symbol</u> <u>Type</u>	G	H	J	T		
C1005 (CC0402)	2.00 ± 0.05	4.00 ± 0.05	Ø 1.5 ^{+0.10} ₀	0.60 ± 0.05		

* The values in the parentheses () are for reference

Appendix 5

Paper Tape



(Unit : mm)


Symbol Type	A	B	C	D	E	F
C1608 (CC0603)	(1.10)	(1.90)				
C2012 (CC0805)	(1.50)	(2.30)	8.00 ± 0.30	3.50 ± 0.05	1.75 ± 0.10	4.00 ± 0.10
C3216 (CC1206)	(1.90)	(3.50)				

Symbol Type	G	H	J	T
C1608 (CC0603)				
C2012 (CC0805)	2.00 ± 0.05	4.00 ± 0.10	Ø 1.5 ^{+0.10} ₀	1.10 max.
C3216 (CC1206)				

* The values in the parentheses () are for reference.

Appendix 6

Plastic Tape



(Unit : mm)


Symbol Type	A	B	C	D	E	F
C2012 (CC0805)	(1.50)	(2.30)				
C3216 (CC1206)	(1.90)	(3.50)	8.00 ± 0.30 [12.0 ± 0.30]	3.50 ± 0.05 [5.50 ± 0.05]	1.75 ± 0.10	4.00 ± 0.10
C3225 (CC1210)	(2.90)	(3.60)				
Symbol Type	G	H	J	K	t	Q
C2012 (CC0805)					0.30 max.	
C3216 (CC1206)	2.00 ± 0.05	4.00 ± 0.10	Ø 1.5 ^{+0.10} ₀	2.50 max. [6.50 max.]		Ø 0.50 min.
C3225 (CC1210)					0.60 max.	

* The values in the parentheses () are for reference.

* As for 2.5mm thickness products, apply values in the brackets [].

Appendix 7

Plastic Tape



(Unit : mm)


Symbol Type	A	B	C	D	E	F
C4532 (CC1812)	(3.60)	(4.90)				
C5750 (CC2220)	(5.40)	(6.10)	12.0 ± 0.30	5.50 ± 0.05	1.75 ± 0.10	8.00 ± 0.10
Symbol Type	G	H	J	K	t	Q
C4532 (CC1812)	2.00 ± 0.05	4.00 ± 0.10	Ø 1.5 ^{+0.10} ₀	6.50 max.	0.60 max.	Ø 1.50 min.
C5750 (CC2220)						

* The values in the parentheses () are for reference.

Appendix 8

C0603, C1005, C1608, C2012, C3216, C3225 (As for C3225 type, any thickness of the item except 2.5mm)

(Material : Polystyrene)




(Unit : mm)

Symbol	A	B	C	D	E	W ₁
Dimension	$\varnothing 178 \pm 2.0$	$\varnothing 60 \pm 2.0$	$\varnothing 13 \pm 0.5$	$\varnothing 21 \pm 0.8$	2.0 ± 0.5	9.0 ± 0.3
Symbol		W ₂				
Dimension		13.0 ± 1.4				

Appendix 9

C3225, C4532, C5750 (As for C3225 type, applied to 2.5mm thickness products)

(Material : Polystyrene)




(Unit : mm)

Symbol	A	B	C	D	E	W ₁
Dimension	$\varnothing 178 \pm 2.0$	$\varnothing 60 \pm 2.0$	$\varnothing 13 \pm 0.5$	$\varnothing 21 \pm 0.8$	2.0 ± 0.5	13.0 ± 0.3
Symbol		W ₂				
Dimension		17.0 ± 1.4				

Appendix 10

C1005, C1608, C2012, C3216, C3225 (As for C3225 type, any thickness of the item except 2.5mm)

(Material : Polystyrene)




(Unit : mm)

Symbol	A	B	C	D	E	W
Dimension	$\varnothing 382$ max. (Nominal $\varnothing 330$)	$\varnothing 50$ min.	$\varnothing 13 \pm 0.5$	$\varnothing 21 \pm 0.8$	2.0 ± 0.5	10.0 ± 1.5
Symbol	t	r				
Dimension	2.0 ± 0.5	1.0				

Appendix 11

C3225, C4532, C5750 (As for C3225 type, applied to 2.5mm thickness products)

(Material : Polystyrene)



(Unit : mm)

Symbol	A	B	C	D	E	W
Dimension	$\varnothing 382$ max. (Nominal $\varnothing 330$)	$\varnothing 50$ min.	$\varnothing 13 \pm 0.5$	$\varnothing 21 \pm 0.8$	2.0 ± 0.5	14.0 ± 1.5
Symbol	t	r				
Dimension	2.0 ± 0.5	1.0				

16. Table A (TDK products line up)

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.		Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life		Tape packaging materials	Qty. per 1 reel		
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage				ΔC/C	ΔC/C	ΔC/C	Test voltage	φ178mm	φ330mm
1	C0603CG1E0R5C	0.60±0.03	0.30±0.03	0.30±0.03	410			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
2	C0603CG1E010C	0.60±0.03	0.30±0.03	0.30±0.03	420			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
3	C0603CG1E1R5C	0.60±0.03	0.30±0.03	0.30±0.03	430			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
4	C0603CG1E020C	0.60±0.03	0.30±0.03	0.30±0.03	440			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
5	C0603CG1E2R2C	0.60±0.03	0.30±0.03	0.30±0.03	444			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
6	C0603CG1E030C	0.60±0.03	0.30±0.03	0.30±0.03	460			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
7	C0603CG1E3R3C	0.60±0.03	0.30±0.03	0.30±0.03	466			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
8	C0603CG1E040C	0.60±0.03	0.30±0.03	0.30±0.03	480			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
9	C0603CG1E4R7C	0.60±0.03	0.30±0.03	0.30±0.03	494			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
10	C0603CG1E050C	0.60±0.03	0.30±0.03	0.30±0.03	500			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
11	C0603CG1E060D	0.60±0.03	0.30±0.03	0.30±0.03	520			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
12	C0603CG1E6R8D	0.60±0.03	0.30±0.03	0.30±0.03	536			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
13	C0603CG1E070D	0.60±0.03	0.30±0.03	0.30±0.03	540			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
14	C0603CG1E080D	0.60±0.03	0.30±0.03	0.30±0.03	560			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
15	C0603CG1E090D	0.60±0.03	0.30±0.03	0.30±0.03	580			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
16	C0603CG1E100D	0.60±0.03	0.30±0.03	0.30±0.03	600			1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	±0.3pF	20 x R.V.	Paper	15,000	50,000
17	C0603CG1E120J	0.60±0.03	0.30±0.03	0.30±0.03	640			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±3.0%	20 x R.V.	Paper	15,000	50,000
18	C0603CG1E150J	0.60±0.03	0.30±0.03	0.30±0.03	700			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±3.0%	20 x R.V.	Paper	15,000	50,000
19	C0603CG1E180J	0.60±0.03	0.30±0.03	0.30±0.03	760			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±3.0%	20 x R.V.	Paper	15,000	50,000
20	C0603CG1E220J	0.60±0.03	0.30±0.03	0.30±0.03	840			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±3.0%	20 x R.V.	Paper	15,000	50,000
21	C0603CG1E270J	0.60±0.03	0.30±0.03	0.30±0.03	940			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±3.0%	20 x R.V.	Paper	15,000	50,000
22	C0603CG1E330J	0.60±0.03	0.30±0.03	0.30±0.03	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±3.0%	20 x R.V.	Paper	15,000	50,000
23	C0603CG1E390J	0.60±0.03	0.30±0.03	0.30±0.03	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±3.0%	20 x R.V.	Paper	15,000	50,000
24	C0603CG1E470J	0.60±0.03	0.30±0.03	0.30±0.03	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±3.0%	20 x R.V.	Paper	15,000	50,000
25	C0603CG1E560J	0.60±0.03	0.30±0.03	0.30±0.03	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±3.0%	20 x R.V.	Paper	15,000	50,000
26	C0603CG1E680J	0.60±0.03	0.30±0.03	0.30±0.03	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±3.0%	20 x R.V.	Paper	15,000	50,000
27	C0603CG1E820J	0.60±0.03	0.30±0.03	0.30±0.03	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±3.0%	20 x R.V.	Paper	15,000	50,000
28	C0603CG1E101J	0.60±0.03	0.30±0.03	0.30±0.03	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±3.0%	20 x R.V.	Paper	15,000	50,000
29	C0603SR1E101K	0.60±0.03	0.30±0.03	0.30±0.03	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
30	C0603SR1E151K	0.60±0.03	0.30±0.03	0.30±0.03	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
31	C0603SR1E221K	0.60±0.03	0.30±0.03	0.30±0.03	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
32	C0603SR1E331K	0.60±0.03	0.30±0.03	0.30±0.03	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
33	C0603SR1E471K	0.60±0.03	0.30±0.03	0.30±0.03	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
34	C0603SR1E681K	0.60±0.03	0.30±0.03	0.30±0.03	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
35	C0603SR1E102K	0.60±0.03	0.30±0.03	0.30±0.03	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
36	C0603SR1E152K	0.60±0.03	0.30±0.03	0.30±0.03	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
37	C0603SR1E222K	0.60±0.03	0.30±0.03	0.30±0.03	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
38	C0603SR1E332K	0.60±0.03	0.30±0.03	0.30±0.03	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
39	C0603SR1C472K	0.60±0.03	0.30±0.03	0.30±0.03	0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
40	C0603SR1A682K	0.60±0.03	0.30±0.03	0.30±0.03	0.05	1kHz	0.2Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
41	C0603SR1A103K	0.60±0.03	0.30±0.03	0.30±0.03	0.05	1kHz	0.2Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
42	C0603SR0J153K	0.60±0.03	0.30±0.03	0.30±0.03	0.05	1kHz	0.2Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	20 x R.V.	Paper	15,000	50,000		
43	C0603SR0J223K	0.60±0.03	0.30±0.03	0.30±0.03	0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	20 x R.V.	Paper	15,000	50,000		
44	C0603SR0J333K	0.60±0.03	0.30±0.03	0.30±0.03	0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	20 x R.V.	Paper	15,000	50,000		
45	C0603SR0J473K	0.60±0.03	0.30±0.03	0.30±0.03	0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	20 x R.V.	Paper	15,000	50,000		
46	C0603SR0J683K	0.60±0.03	0.30±0.03	0.30±0.03	0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	20 x R.V.	Paper	15,000	50,000		
47	C0603SR0J104K	0.60±0.03	0.30±0.03	0.30±0.03	0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	20 x R.V.	Paper	15,000	50,000		

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.		Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life			Tape packaging materials	Qty. per 1 reel	
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage				ΔC/C	ΔC/C	ΔC/C	Test voltage	φ178mm	φ330mm
48	C0603Y5V1C103Z	0.60±0.03	0.30±0.03	0.30±0.03		0.10	1kHz	1.0Vrms	±20%		±30%	±30%	±30%	2.0 x R.V.	Paper	15,000	50,000	
49	C1005CG1H05C	1.00±0.05	0.50±0.05	0.50±0.05	410		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
50	C1005CG1H010C	1.00±0.05	0.50±0.05	0.50±0.05	420		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
51	C1005CG1H185C	1.00±0.05	0.50±0.05	0.50±0.05	430		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
52	C1005CG1H020C	1.00±0.05	0.50±0.05	0.50±0.05	440		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
53	C1005CG1H2R2C	1.00±0.05	0.50±0.05	0.50±0.05	444		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
54	C1005CG1H030C	1.00±0.05	0.50±0.05	0.50±0.05	460		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
55	C1005CG1H13R3C	1.00±0.05	0.50±0.05	0.50±0.05	466		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
56	C1005CG1H040C	1.00±0.05	0.50±0.05	0.50±0.05	480		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
57	C1005CG1H4R7C	1.00±0.05	0.50±0.05	0.50±0.05	494		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
58	C1005CG1H1050C	1.00±0.05	0.50±0.05	0.50±0.05	500		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
59	C1005CG1H060D	1.00±0.05	0.50±0.05	0.50±0.05	520		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
60	C1005CG1H6R8D	1.00±0.05	0.50±0.05	0.50±0.05	536		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
61	C1005CG1H070D	1.00±0.05	0.50±0.05	0.50±0.05	540		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
62	C1005CG1H080D	1.00±0.05	0.50±0.05	0.50±0.05	560		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
63	C1005CG1H090D	1.00±0.05	0.50±0.05	0.50±0.05	580		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
64	C1005CG1H100D	1.00±0.05	0.50±0.05	0.50±0.05	600		1MHz	0.5-Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	2.0 x R.V.	Paper	10,000	50,000		
65	C1005CG1H120J	1.00±0.05	0.50±0.05	0.50±0.05	640		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
66	C1005CG1H150J	1.00±0.05	0.50±0.05	0.50±0.05	700		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
67	C1005CG1H180J	1.00±0.05	0.50±0.05	0.50±0.05	760		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
68	C1005CG1H220J	1.00±0.05	0.50±0.05	0.50±0.05	840		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
69	C1005CG1H270J	1.00±0.05	0.50±0.05	0.50±0.05	940		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
70	C1005CG1H1330J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
71	C1005CG1H1390J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
72	C1005CG1H470J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
73	C1005CG1H1470J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
74	C1005CG1H1560J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
75	C1005CG1H1680J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
76	C1005CG1H1820J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
77	C1005CG1H101J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
78	C1005CG1H112J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
79	C1005CG1H115J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
80	C1005CG1H221J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
81	C1005CG1H271J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
82	C1005CG1H331J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
83	C1005CG1H391J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		
84	C1005CG1H471J	1.00±0.05	0.50±0.05	0.50±0.05	1,000		1MHz	0.5-Vrms	±2.5%	±5.0%	±7.5%	±3.0%	2.0 x R.V.	Paper	10,000	50,000		

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.		Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life			Tape packaging materials	Qty. per 1 reel		
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage				ΔC/C	ΔC/C	ΔC/C	Test voltage	φ178mm	φ330mm	
85		C1005X5R1E333K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	20 x R.V.	Paper	10,000	50,000
86		C1005X5R1E473K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	20 x R.V.	Paper	10,000	50,000
87		C1005X5R1E683K	1.00±0.05	0.50±0.05	0.50±0.05		0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
88		C1005X5R1E104K	1.00±0.05	0.50±0.05	0.50±0.05		0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
89		C1005X5R1C683K	1.00±0.05	0.50±0.05	0.50±0.05		0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	20 x R.V.	Paper	10,000	50,000
90		C1005X5R1C104K	1.00±0.05	0.50±0.05	0.50±0.05		0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	20 x R.V.	Paper	10,000	50,000
91		C1005X5R1C154K	1.00±0.05	0.50±0.05	0.50±0.05		0.05	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	15 x R.V.	Paper	10,000	50,000
92		C1005X5R1C224K	1.00±0.05	0.50±0.05	0.50±0.05		0.05	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	15 x R.V.	Paper	10,000	50,000
93		C1005X5R1C334K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
94		C1005X5R1C474K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
95		C1005X5R1C684K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
96		C1005X5R1C105K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
97		C1005X5R1A154K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
98		C1005X5R1A224K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
99		C1005X5R1A334K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
100		C1005X5R1A474K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
101		C1005X5R1A684K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
102		C1005X5R1A105K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
103		C1005X5R0J154K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	15 x R.V.	Paper	10,000	50,000
104		C1005X5R0J224K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	15 x R.V.	Paper	10,000	50,000
105		C1005X5R0J334K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	15 x R.V.	Paper	10,000	50,000
106		C1005X5R0J474K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	15 x R.V.	Paper	10,000	50,000
107		C1005X5R0J684K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
108		C1005X5R0J105K	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
109		C1005X5R0J155M	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	15 x R.V.	Paper	10,000	50,000
110		C1005X5R0J225M	1.00±0.05	0.50±0.05	0.50±0.05		0.10	1kHz	0.5Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	15 x R.V.	Paper	10,000	50,000
111		C1005X5R1H221K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
112		C1005X5R1H331K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
113		C1005X5R1H471K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
114		C1005X5R1H681K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
115		C1005X5R1H102K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
116		C1005X5R1H152K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
117		C1005X5R1H222K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
118		C1005X5R1H332K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
119		C1005X5R1H472K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
120		C1005X5R1H682K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
121		C1005X5R1E103K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
122		C1005X5R1E153K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
123		C1005X5R1E223K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Paper	10,000	50,000
124		C1005X5R1E333K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
125		C1005X5R1E473K	1.00±0.05	0.50±0.05	0.50±0.05		0.03	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
126		C1005X5R1C683K	1.00±0.05	0.50±0.05	0.50±0.05		0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000
127		C1005X5R1C104K	1.00±0.05	0.50±0.05	0.50±0.05		0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	10,000	50,000

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.		Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life			Tape packaging materials	Qty. per 1 reel	
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage				ΔC/C	ΔC/C	ΔC/C	Test voltage	φ178mm	φ330mm
128	C1005Y5V1E104Z	1.00±0.05	0.50±0.05	0.50±0.05		0.075	1kHz	1.0Vrms	+20%		±30%	±30%	±30%	±30%	20 x R.V.	Paper	10,000	50,000
129	C1005Y5V1E224Z	1.00±0.05	0.50±0.05	0.50±0.05		0.075	1kHz	1.0Vrms	+20%		±30%	±30%	±30%	±30%	20 x R.V.	Paper	10,000	50,000
130	C1005Y5V1A474Z	1.00±0.05	0.50±0.05	0.50±0.05		0.125	1kHz	0.2Vrms	+20%		±30%	±30%	±30%	±30%	20 x R.V.	Paper	10,000	50,000
131	C1005Y5V0J105Z	1.00±0.05	0.50±0.05	0.50±0.05		0.20	1kHz	0.2Vrms	+20%		±30%	±40%	±40%	±40%	20 x R.V.	Paper	10,000	50,000
132	C1608CG0G1H05C	1.60±0.10	0.80±0.10	0.80±0.10	410		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
133	C1608CG0G1H010C	1.60±0.10	0.80±0.10	0.80±0.10	420		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
134	C1608CG0G1H1R5C	1.60±0.10	0.80±0.10	0.80±0.10	430		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
135	C1608CG0G1H020C	1.60±0.10	0.80±0.10	0.80±0.10	440		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
136	C1608CG0G1H2R2C	1.60±0.10	0.80±0.10	0.80±0.10	444		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
137	C1608CG0G1H030C	1.60±0.10	0.80±0.10	0.80±0.10	460		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
138	C1608CG0G1H3R3C	1.60±0.10	0.80±0.10	0.80±0.10	466		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
139	C1608CG0G1H404C	1.60±0.10	0.80±0.10	0.80±0.10	480		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
140	C1608CG0G1H4R7C	1.60±0.10	0.80±0.10	0.80±0.10	494		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
141	C1608CG0G1H050C	1.60±0.10	0.80±0.10	0.80±0.10	500		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
142	C1608CG0G1H060D	1.60±0.10	0.80±0.10	0.80±0.10	520		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
143	C1608CG0G1H6R8D	1.60±0.10	0.80±0.10	0.80±0.10	536		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
144	C1608CG0G1H070D	1.60±0.10	0.80±0.10	0.80±0.10	540		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
145	C1608CG0G1H080D	1.60±0.10	0.80±0.10	0.80±0.10	560		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
146	C1608CG0G1H090D	1.60±0.10	0.80±0.10	0.80±0.10	580		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
147	C1608CG0G1H100D	1.60±0.10	0.80±0.10	0.80±0.10	600		1MHz	0.5-5Vrms	±0.25pF	±0.5pF	±0.75pF	±0.3pF	20 x R.V.	Paper	4,000	10,000		
148	C1608CG0G1H120J	1.60±0.10	0.80±0.10	0.80±0.10	640		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
149	C1608CG0G1H150J	1.60±0.10	0.80±0.10	0.80±0.10	700		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
150	C1608CG0G1H180J	1.60±0.10	0.80±0.10	0.80±0.10	760		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
151	C1608CG0G1H220J	1.60±0.10	0.80±0.10	0.80±0.10	840		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
152	C1608CG0G1H270J	1.60±0.10	0.80±0.10	0.80±0.10	940		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
153	C1608CG0G1H330J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
154	C1608CG0G1H390J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
155	C1608CG0G1H470J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
156	C1608CG0G1H560J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
157	C1608CG0G1H680J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
158	C1608CG0G1H820J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
159	C1608CG0G1H101J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
160	C1608CG0G1H121J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
161	C1608CG0G1H151J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
162	C1608CG0G1H181J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
163	C1608CG0G1H221J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
164	C1608CG0G1H271J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
165	C1608CG0G1H331J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
166	C1608CG0G1H391J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
167	C1608CG0G1H471J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
168	C1608CG0G1H561J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
169	C1608CG0G1H681J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
170	C1608CG0G1H821J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
171	C1608CG0G1H102J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
172	C1608CG0G1H122J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
173	C1608CG0G1H152J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
174	C1608CG0G1H182J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
175	C1608CG0G1H222J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
176	C1608CG0G1H272J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
177	C1608CG0G1H332J	1.60±0.10	0.80±0.10	0.80±0.10	1,000		1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.		Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life			Tape packaging materials	Qty. per 1 reel	
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage				ΔC/C	ΔC/C	ΔC/C	Test voltage	φ178mm	φ330mm
178		C1608X5R1E224K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	2.0 x R.V.	Paper	4,000	10,000
179		C1608X5R1E334K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
180		C1608X5R1E474K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
181		C1608X5R1E684K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
182		C1608X5R1E105K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
183		C1608X5R1C474K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	2.0 x R.V.	Paper	4,000	10,000
184		C1608X5R1C684K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	2.0 x R.V.	Paper	4,000	10,000
185		C1608X5R1C105K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	2.0 x R.V.	Paper	4,000	10,000
186		C1608X5R1C155K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	1.5 x R.V.	Paper	4,000	10,000
187		C1608X5R1C225K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	1.5 x R.V.	Paper	4,000	10,000
188		C1608X5R1A684K	1.60±0.15±0.10	0.80±0.15±0.10	0.80±0.15±0.10	0.05	1kHz	0.2Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
189		C1608X5R1A105K	1.60±0.15±0.10	0.80±0.15±0.10	0.80±0.15±0.10	0.05	1kHz	0.2Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
190		C1608X5R1A155K	1.60±0.15±0.10	0.80±0.15±0.10	0.80±0.15±0.10	0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
191		C1608X5R1A225K	1.60±0.15±0.10	0.80±0.15±0.10	0.80±0.15±0.10	0.10	1kHz	0.2Vrms	±15%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
192		C1608X5R1A335K	1.60±0.10	0.80±0.10	0.80±0.10	0.10	1kHz	0.2Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	1.5 x R.V.	Paper	4,000	10,000
193		C1608X5R1A475K	1.60±0.10	0.80±0.10	0.80±0.10	0.10	1kHz	0.2Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
194		C1608X5R0U105K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	0.2Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
195		C1608X5R0U158K	1.60±0.10	0.80±0.10	0.80±0.10	0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	1.5 x R.V.	Paper	4,000	10,000
196		C1608X5R0U225K	1.60±0.10	0.80±0.10	0.80±0.10	0.10	1kHz	0.2Vrms	±15%	±25%	±25%	±25%	±25%	±25%	1.5 x R.V.	Paper	4,000	10,000
197		C1608X5R0U335K	1.60±0.15±0.10	0.80±0.15±0.10	0.80±0.15±0.10	0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
198		C1608X5R0U475K	1.60±0.15±0.10	0.80±0.15±0.10	0.80±0.15±0.10	0.10	1kHz	0.5Vrms	±15%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
199		C1608X5R0U685K	1.60±0.20±0.10	0.80±0.20±0.10	0.80±0.20±0.10	0.10	1kHz	0.2Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
200		C1608X5R0U106M	1.60±0.20±0.10	0.80±0.20±0.10	0.80±0.20±0.10	0.10	1kHz	0.2Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
201		C1608X7R1H102K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
202		C1608X7R1H152K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
203		C1608X7R1H222K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
204		C1608X7R1H332K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
205		C1608X7R1H472K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
206		C1608X7R1H682K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
207		C1608X7R1H103K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
208		C1608X7R1H153K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
209		C1608X7R1H223K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
210		C1608X7R1H333K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
211		C1608X7R1H473K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
212		C1608X7R1H683K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
213		C1608X7R1H104K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
214		C1608X7R1E104K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
215		C1608X7R1E154K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±12.5%	±12.5%	±12.5%	2.0 x R.V.	Paper	4,000	10,000
216		C1608X7R1E224K	1.60±0.10	0.80±0.10	0.80±0.10	0.03	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
217		C1608X7R1C334K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
218		C1608X7R1C474K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
219		C1608X7R1C684K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000
220		C1608X7R1C105K	1.60±0.10	0.80±0.10	0.80±0.10	0.05	1kHz	0.1Vrms	±12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Paper	4,000	10,000

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.			Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life			Tape packaging materials	Qty. per 1 reel	
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage	ΔC/C				ΔC/C	ΔC/C	Test voltage		φ178mm	φ330mm
221	C1608Y5V1H104Z	1.60±0.10	0.80±0.10	0.80±0.10		0.05	1kHz	1.0Vrms	+20%	±30%	±30%	±30%	±30%	±30%	20 x R.V.	Paper	4,000	10,000	
222	C1608Y5V1H224Z	1.60±0.10	0.80±0.10	0.80±0.10		0.05	1kHz	1.0Vrms	+20%	±30%	±30%	±30%	±30%	±30%	20 x R.V.	Paper	4,000	10,000	
223	C1608Y5V1H474Z	1.60±0.10	0.80±0.10	0.80±0.10		0.05	1kHz	1.0Vrms	+20%	±30%	±30%	±30%	±30%	±30%	20 x R.V.	Paper	4,000	10,000	
224	C1608Y5V1E105Z	1.60±0.10	0.80±0.10	0.80±0.10		0.075	1kHz	1.0Vrms	+20%	±30%	±30%	±30%	±30%	±30%	20 x R.V.	Paper	4,000	10,000	
225	C1608Y5V1C225Z	1.60±0.10	0.80±0.10	0.80±0.10		0.10	1kHz	1.0Vrms	+20%	±30%	±30%	±30%	±30%	±30%	20 x R.V.	Paper	4,000	10,000	
226	C1608Y5V0J475Z	1.60±0.10	0.80±0.10	0.80±0.10		0.20	1kHz	0.2Vrms	+20%	±30%	±30%	±40%	±40%	±40%	20 x R.V.	Paper	4,000	10,000	
227	C2012CG1H392J	2.00±0.20	1.25±0.20	0.85±0.15	1,000		1kHz	0.5-5Vrms	+2.5%	±5.0%	±7.5%	±3.0%	±2.0%	±3.0%	20 x R.V.	Paper	4,000	10,000	
228	C2012CG1H4472J	2.00±0.20	1.25±0.20	0.85±0.15	1,000		1kHz	0.5-5Vrms	+2.5%	±5.0%	±7.5%	±3.0%	±2.0%	±3.0%	20 x R.V.	Paper	4,000	10,000	
229	C2012CG1H562J	2.00±0.20	1.25±0.20	0.85±0.15	1,000		1kHz	0.5-5Vrms	+2.5%	±5.0%	±7.5%	±3.0%	±2.0%	±3.0%	20 x R.V.	Paper	4,000	10,000	
230	C2012CG1H682J	2.00±0.20	1.25±0.20	1.25±0.20	1,000		1kHz	0.5-5Vrms	+2.5%	±5.0%	±7.5%	±3.0%	±2.0%	±3.0%	20 x R.V.	Plastic	2,000	10,000	
231	C2012CG1H822J	2.00±0.20	1.25±0.20	1.25±0.20	1,000		1kHz	0.5-5Vrms	+2.5%	±5.0%	±7.5%	±3.0%	±2.0%	±3.0%	20 x R.V.	Plastic	2,000	10,000	
232	C2012CG1H103J	2.00±0.20	1.25±0.20	1.25±0.20	1,000		1kHz	0.5-5Vrms	+2.5%	±5.0%	±7.5%	±3.0%	±2.0%	±3.0%	20 x R.V.	Plastic	2,000	10,000	
233	C2012X5R1E684K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Plastic	2,000	10,000	
234	C2012X5R1E105K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Plastic	2,000	10,000	
235	C2012X5R1E155K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Plastic	2,000	10,000	
236	C2012X5R1E225K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	1.0Vrms	+12.5%	±25%	±25%	±25%	±25%	±25%	15 x R.V.	Plastic	2,000	10,000	
237	C2012X5R1E335K	2.00±0.20	1.25±0.20	1.25±0.20		0.075	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	15 x R.V.	Plastic	2,000	10,000	
238	C2012X5R1E475K	2.00±0.20	1.25±0.20	1.25±0.20		0.075	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	15 x R.V.	Plastic	2,000	10,000	
239	C2012X5R1C105K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Plastic	2,000	10,000	
240	C2012X5R1C155K	2.00±0.20	1.25±0.20	1.25±0.20		0.075	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Plastic	2,000	10,000	
241	C2012X5R1C225K	2.00±0.20	1.25±0.20	1.25±0.20		0.075	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Plastic	2,000	10,000	
242	C2012X5R1C335K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	0.1Vrms	+12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Plastic	2,000	10,000	
243	C2012X5R1C475K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	0.1Vrms	+12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Plastic	2,000	10,000	
244	C2012X5R1C106K	2.00±0.20	1.25±0.20	1.25±0.20		0.10	1kHz	1.0Vrms	+12.5%	±25%	±25%	±25%	±25%	±25%	15 x R.V.	Plastic	2,000	10,000	
245	C2012X5R1A335K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	0.1Vrms	+12.5%	±25%	±25%	±25%	±25%	±25%	20 x R.V.	Plastic	2,000	10,000	
246	C2012X5R1A475K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	0.1Vrms	+12.5%	±25%	±25%	±25%	±25%	±25%	20 x R.V.	Plastic	2,000	10,000	
247	C2012X5R1A685K	2.00±0.20	1.25±0.20	1.25±0.20		0.10	1kHz	0.5Vrms	+15%	±25%	±25%	±25%	±25%	±25%	R.V.	Plastic	2,000	10,000	
248	C2012X5R1A106K	2.00±0.20	1.25±0.20	1.25±0.20		0.10	1kHz	0.2Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	R.V.	Plastic	2,000	10,000	
249	C2012X5R0J106K (T=0.85)	2.00±0.20	1.25±0.20	1.25±0.20		0.85±0.15	0.10	1kHz	0.5Vrms	+15%	±25%	±25%	±25%	±25%	±25%	R.V.	Plastic	4,000	10,000
250	C2012X5R0J106K (T=1.25)	2.00±0.20	1.25±0.20	1.25±0.20		0.10	1kHz	0.2Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	15 x R.V.	Plastic	2,000	10,000	
251	C2012X5R0J156M	2.00±0.20	1.25±0.20	1.25±0.20		0.15	120Hz	0.5Vrms	+12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Plastic	2,000	10,000	
252	C2012X5R0J226M	2.00±0.20	1.25±0.20	1.25±0.20		0.15	120Hz	0.5Vrms	+12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Plastic	2,000	10,000	
253	C2012X7R1H154K	2.00±0.20	1.25±0.20	1.25±0.20		0.03	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Plastic	2,000	10,000	
254	C2012X7R1H224K	2.00±0.20	1.25±0.20	1.25±0.20		0.03	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Plastic	2,000	10,000	
255	C2012X7R1H334K	2.00±0.20	1.25±0.20	1.25±0.20		0.03	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Plastic	2,000	10,000	
256	C2012X7R1E474K	2.00±0.20	1.25±0.20	1.25±0.20		0.03	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Plastic	2,000	10,000	
257	C2012X7R1E684K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	15 x R.V.	Plastic	2,000	10,000	
258	C2012X7R1E105K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	15 x R.V.	Plastic	2,000	10,000	
259	C2012X7R1E155K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	15 x R.V.	Plastic	2,000	10,000	
260	C2012X7R1C105K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	20 x R.V.	Plastic	2,000	10,000	
261	C2012X7R1C155K	2.00±0.20	1.25±0.20	1.25±0.20		0.075	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	15 x R.V.	Plastic	2,000	10,000	
262	C2012X7R1C225K	2.00±0.20	1.25±0.20	1.25±0.20		0.075	1kHz	1.0Vrms	+7.5%	±12.5%	±12.5%	±15%	±15%	±15%	15 x R.V.	Plastic	2,000	10,000	
263	C2012X7R1A335K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	0.1Vrms	+12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Plastic	2,000	10,000	
264	C2012X7R1A475K	2.00±0.20	1.25±0.20	1.25±0.20		0.05	1kHz	0.1Vrms	+12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Plastic	2,000	10,000	
265	C2012X7R1A106K	2.00±0.20	1.25±0.20	1.25±0.20		0.10	1kHz	0.5Vrms	+12.5%	±25%	±25%	±25%	±25%	±25%	R.V.	Plastic	2,000	10,000	
266	C2012X7R0J106K	2.00±0.20	1.25±0.20	1.25±0.20		0.10	1kHz	0.5Vrms	+12.5%	±25%	±25%	±25%	±25%	±25%	15 x R.V.	Plastic	2,000	10,000	

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.		Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life			Tape packaging materials	Qty. per 1 reel	
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage				ΔC/C	ΔC/C	ΔC/C	Test voltage	φ178mm	φ330mm
267	C2012Y5V1H105Z	2.00±0.20	1.25±0.20	0.85±0.15			0.05	1kHz	1.0Vrms	+20%	±30%	±30%	±30%	±30%	2.0 x R.V.	Paper	4.000	10,000
268	C2012Y5V1H225Z	2.00±0.20	1.25±0.20	1.25±0.20			0.05	1kHz	1.0Vrms	+20%	±30%	±30%	±30%	±30%	2.0 x R.V.	Plastic	2.000	10,000
269	C2012Y5V1E475Z	2.00±0.20	1.25±0.20	1.25±0.20			0.075	1kHz	1.0Vrms	+20%	±30%	±30%	±30%	±30%	2.0 x R.V.	Plastic	2.000	10,000
270	C2012Y5V1C106Z	2.00±0.20	1.25±0.20	1.25±0.20			0.10	1kHz	1.0Vrms	+20%	±30%	±30%	±30%	±30%	2.0 x R.V.	Plastic	2.000	10,000
271	C2012Y5V0J226Z	2.00±0.20	1.25±0.20	1.25±0.20			0.20	120Hz	0.5Vrms	+20%	±30%	±40%	±40%	±40%	2.0 x R.V.	Plastic	2.000	10,000
272	C3216CG1H153K	3.20±0.20	1.60±0.20	1.15±0.15	1,000			1kHz	0.5-5Vrms	+2.5%	±5.0%	±7.5%	±3.0%	±7.5%	2.0 x R.V.	Plastic	2.000	10,000
273	C3216CG1H223K	3.20±0.20	1.60±0.20	1.15±0.15	1,000			1kHz	0.5-5Vrms	+2.5%	±5.0%	±7.5%	±3.0%	±7.5%	2.0 x R.V.	Plastic	2.000	10,000
274	C3216CG1H333K	3.20±0.20	1.60±0.20	1.60±0.20	1,000			1kHz	0.5-5Vrms	+2.5%	±5.0%	±7.5%	±3.0%	±7.5%	2.0 x R.V.	Plastic	2.000	8,000
275	C3216X5R1H105K	3.20±0.20	1.60±0.20	1.60±0.20			0.05	1kHz	1.0Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	2.0 x R.V.	Plastic	2.000	8,000
276	C3216X5R1E155K	3.20±0.20	1.60±0.20	1.60±0.20			0.03	1kHz	1.0Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	2.0 x R.V.	Plastic	2.000	8,000
277	C3216X5R1E225K	3.20±0.20	1.60±0.20	1.60±0.20			0.03	1kHz	1.0Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	2.0 x R.V.	Plastic	2.000	8,000
278	C3216X5R1E335K	3.20±0.20	1.60±0.20	1.60±0.20			0.03	1kHz	1.0Vrms	+12.5%	±25%	±25%	±25%	±25%	2.0 x R.V.	Plastic	2.000	8,000
279	C3216X5R1E475K	3.20±0.20	1.60±0.20	1.60±0.20			0.03	1kHz	1.0Vrms	+12.5%	±25%	±25%	±25%	±25%	2.0 x R.V.	Plastic	2.000	8,000
280	C3216X5R1C685K	3.20±0.20	1.60±0.20	1.60±0.20			0.05	1kHz	0.1Vrms	+12.5%	±25%	±25%	±25%	±25%	2.0 x R.V.	Plastic	2.000	8,000
281	C3216X5R1C106K	3.20±0.20	1.60±0.20	1.60±0.20			0.05	1kHz	0.1Vrms	+12.5%	±25%	±25%	±25%	±25%	2.0 x R.V.	Plastic	2.000	8,000
282	C3216X5R1A106K (T=0.85)	3.20±0.20	1.60±0.20	0.85±0.15			0.075	1kHz	0.2Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	R.V.	Plastic	4.000	10,000
283	C3216X5R1A106K (T=1.60)	3.20±0.30±0.10	1.60±0.30±0.10	1.60±0.30±0.10			0.075	1kHz	0.2Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	2.0 x R.V.	Plastic	2.000	8,000
284	C3216X5R0J106K	3.20±0.20	1.60±0.20	1.60±0.20			0.075	1kHz	0.2Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	2.0 x R.V.	Plastic	4.000	10,000
285	C3216X5R0J156M	3.20±0.20	1.60±0.20	1.60±0.20			0.075	120Hz	0.5Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	2.0 x R.V.	Plastic	2.000	8,000
286	C3216X5R0J226M (T=0.85)	3.20±0.20	1.60±0.20	0.85±0.15			0.15	120Hz	0.5Vrms	+12.5%	±25%	±25%	±25%	±25%	R.V.	Plastic	4.000	10,000
287	C3216X5R0J226M (T=1.60)	3.20±0.30±0.10	1.60±0.30±0.10	1.60±0.30±0.10			0.075	120Hz	0.5Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	2.0 x R.V.	Plastic	2.000	8,000
288	C3216X5R0J336M	3.20±0.20	1.60±0.20	1.30±0.20			0.15	120Hz	0.5Vrms	+12.5%	±25%	±25%	±25%	±25%	R.V.	Plastic	2.000	10,000
289	C3216X5R0J476M	3.20±0.20	1.60±0.20	1.60±0.20			0.15	120Hz	0.5Vrms	+12.5%	±25%	±25%	±25%	±25%	R.V.	Plastic	2.000	8,000
290	C3216X7R1H474K	3.20±0.20	1.60±0.20	1.60±0.20			0.03	1kHz	1.0Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	2.0 x R.V.	Plastic	2.000	8,000
291	C3216X7R1H684K	3.20±0.20	1.60±0.20	1.60±0.20			0.03	1kHz	1.0Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	2.0 x R.V.	Plastic	2.000	8,000
292	C3216X7R1H105K	3.20±0.20	1.60±0.20	1.60±0.20			0.05	1kHz	1.0Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	1.5 x R.V.	Plastic	2.000	8,000
293	C3216X7R1E155K	3.20±0.20	1.60±0.20	1.60±0.20			0.03	1kHz	1.0Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	2.0 x R.V.	Plastic	2.000	8,000
294	C3216X7R1E225K	3.20±0.20	1.60±0.20	1.60±0.20			0.03	1kHz	1.0Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	2.0 x R.V.	Plastic	2.000	8,000
295	C3216X7R1E335K	3.20±0.20	1.60±0.20	1.60±0.20			0.03	1kHz	1.0Vrms	+12.5%	±25%	±25%	±25%	±25%	R.V.	Plastic	2.000	8,000
296	C3216X7R1E475K	3.20±0.20	1.60±0.20	1.60±0.20			0.03	1kHz	1.0Vrms	+12.5%	±25%	±25%	±25%	±25%	R.V.	Plastic	2.000	8,000
297	C3216X7R1C475K	3.20±0.20	1.60±0.20	1.60±0.20			0.075	1kHz	1.0Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	1.5 x R.V.	Plastic	2.000	8,000
298	C3216X7R1C685K	3.20±0.20	1.60±0.20	1.60±0.20			0.05	1kHz	0.1Vrms	+12.5%	±25%	±25%	±25%	±25%	R.V.	Plastic	2.000	8,000
299	C3216X7R1C106K	3.20±0.20	1.60±0.20	1.60±0.20			0.05	1kHz	0.1Vrms	+12.5%	±25%	±25%	±25%	±25%	R.V.	Plastic	2.000	8,000
300	C3216X7R1A106K	3.20±0.30±0.10	1.60±0.30±0.10	1.60±0.30±0.10			0.075	1kHz	0.2Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	R.V.	Plastic	2.000	8,000
301	C3216X7R0J106K	3.20±0.20	1.60±0.20	1.60±0.20			0.05	1kHz	0.2Vrms	+7.5%	±12.5%	±15%	±12.5%	±15%	R.V.	Plastic	2.000	8,000

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.		Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life			Tape packaging materials	Qty. per 1 reel	
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage				ΔC/C	ΔC/C	ΔC/C	Test voltage	φ178mm	φ330mm
302	C3216Y5V1H475Z	3.20±0.20	1.60±0.20	1.60±0.20			0.05	1kHz	1.0Vrms	±20%	±30%	±30%	±30%	±30%	2.0 x R.V.	Plastic	2.000	8.000
303	C3216Y5V1E106Z	3.20±0.20	1.60±0.20	1.60±0.20			0.075	1kHz	1.0Vrms	±20%	±30%	±30%	±30%	±30%	2.0 x R.V.	Plastic	2.000	8.000
304	C3216Y5V1C226Z	3.20±0.20	1.60±0.20	1.60±0.20			0.10	120Hz	0.5Vrms	±20%	±30%	±30%	±30%	±30%	2.0 x R.V.	Plastic	2.000	8.000
305	C3216Y5V0J476Z	3.20±0.30/-0.10	1.60±0.30/-0.10	1.60±0.30/-0.10			0.20	120Hz	0.5Vrms	±20%	±30%	±40%	±40%	±40%	2.0 x R.V.	Plastic	2.000	8.000
306	C3225C0G1H473K	3.20±0.40	2.50±0.30	2.00±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±2.0%	2.0 x R.V.	Plastic	1.000	5.000
307	C3225CG1H1683K	3.20±0.40	2.50±0.30	2.00±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±2.0%	2.0 x R.V.	Plastic	1.000	5.000
308	C3225CG1H104K	3.20±0.40	2.50±0.30	2.50±0.30	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	±2.0%	2.0 x R.V.	Plastic	1.000	5.000
309	C3225X5R1H225K	3.20±0.40	2.50±0.30	2.00±0.20			0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	1.000	5.000
310	C3225X5R1H335K	3.20±0.40	2.50±0.30	2.50±0.30			0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	1.000	5.000
311	C3225X5R1E475K	3.20±0.40	2.50±0.30	2.00±0.20			0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	1.000	5.000
312	C3225X5R1E685K	3.20±0.40	2.50±0.30	2.50±0.30			0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	1.000	5.000
313	C3225X5R1E106K	3.20±0.40	2.50±0.30	2.50±0.30			0.03	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	2.0 x R.V.	Plastic	1.000	5.000
314	C3225X5R1C106K	3.20±0.40	2.50±0.30	2.00±0.20			0.075	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	1.000	5.000
315	C3225X5R1C156M	3.20±0.40	2.50±0.30	2.50±0.30			0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	1.000	5.000
316	C3225X5R1C226M	3.20±0.40	2.50±0.30	2.50±0.30			0.05	120Hz	0.5Vrms	±12.5%	±25%	±25%	±25%	±25%	2.0 x R.V.	Plastic	1.000	5.000
317	C3225X5R1A226M	3.20±0.40	2.50±0.30	2.30±0.20			0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	1.000	5.000
318	C3225X5R0J226M	3.20±0.40	2.50±0.30	2.00±0.20			0.05	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	1.000	5.000
319	C3225X5R0J336M	3.20±0.40	2.50±0.30	2.00±0.20			0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	1.000	5.000
320	C3225X5R0J476M	3.20±0.40	2.50±0.30	2.50±0.30			0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	1.000	5.000
321	C3225X5R0J686M	3.20±0.40	2.50±0.30	2.00±0.20			0.15	120Hz	0.5Vrms	±12.5%	±25%	±25%	±25%	±25%	R.V.	Plastic	1.000	5.000
322	C3225X5R0J107M	3.20±0.40	2.50±0.30	2.50±0.30			0.15	120Hz	0.5Vrms	±12.5%	±25%	±25%	±25%	±25%	R.V.	Plastic	1.000	5.000
323	C3225X7R1H105K	3.20±0.40	2.50±0.30	1.60±0.20			0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	2.000	8.000
324	C3225X7R1H115K	3.20±0.40	2.50±0.30	2.00±0.20			0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	1.000	5.000
325	C3225X7R1H225K	3.20±0.40	2.50±0.30	2.00±0.20			0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	1.5 x R.V.	Plastic	1.000	5.000
326	C3225X7R1H335K	3.20±0.40	2.50±0.30	2.50±0.30			0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	1.5 x R.V.	Plastic	1.000	5.000
327	C3225X7R1E335K	3.20±0.40	2.50±0.30	1.60±0.20			0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	2.000	8.000
328	C3225X7R1E475K	3.20±0.40	2.50±0.30	2.00±0.20			0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	2.0 x R.V.	Plastic	1.000	5.000
329	C3225X7R1E685K	3.20±0.40	2.50±0.30	2.50±0.30			0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	1.5 x R.V.	Plastic	1.000	5.000
330	C3225X7R1E106K	3.20±0.40	2.50±0.30	2.50±0.30			0.03	1kHz	1.0Vrms	±12.5%	±25%	±25%	±25%	±25%	R.V.	Plastic	1.000	5.000
331	C3225X7R1C106K	3.20±0.40	2.50±0.30	2.00±0.20			0.075	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	1.5 x R.V.	Plastic	1.000	5.000
332	C3225X7R1C156M	3.20±0.40	2.50±0.30	2.50±0.30			0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	1.5 x R.V.	Plastic	1.000	5.000
333	C3225X7R1C226M	3.20±0.40	2.50±0.30	2.50±0.30			0.05	120Hz	0.5Vrms	±12.5%	±25%	±25%	±25%	±25%	R.V.	Plastic	1.000	5.000
334	C3225X7R1A226M	3.20±0.40	2.50±0.30	2.30±0.20			0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	±15%	R.V.	Plastic	1.000	5.000
335	C3225Y5V1H106Z	3.20±0.40	2.50±0.30	1.60±0.20			0.05	1kHz	1.0Vrms	±20%	±30%	±30%	±30%	±30%	2.0 x R.V.	Plastic	2.000	8.000
336	C3225Y5V1E226Z	3.20±0.40	2.50±0.30	2.00±0.20			0.075	120Hz	0.5Vrms	±20%	±30%	±30%	±30%	±30%	2.0 x R.V.	Plastic	1.000	5.000
337	C3225Y5V1C476Z	3.20±0.40	2.50±0.30	2.30±0.20			0.10	120Hz	0.5Vrms	±20%	±30%	±30%	±30%	±30%	2.0 x R.V.	Plastic	1.000	5.000
338	C3225Y5V1A476Z	3.20±0.40	2.50±0.30	2.00±0.20			0.125	120Hz	0.5Vrms	±20%	±30%	±30%	±30%	±30%	2.0 x R.V.	Plastic	1.000	5.000
339	C3225Y5V0J107Z	3.20±0.40	2.50±0.30	2.50±0.30			0.20	120Hz	0.5Vrms	±20%	±30%	±40%	±40%	±40%	2.0 x R.V.	Plastic	1.000	5.000

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.		Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life			Tape packaging materials	Qty. per 1 reel	
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage				ΔC/C	ΔC/C	ΔC/C	Test voltage	φ178mm	φ330mm
340	C4532C0G1H154K	4.50±0.40	3.20±0.40	2.50±0.30	1.000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	500	3,000	
341	C4532C0G1H224K	4.50±0.40	3.20±0.40	3.20±0.40	1.000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	500	2,000	
342	C4532X5R1H475K	4.50±0.40	3.20±0.40	2.00±0.20		0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	1,000	3,000		
343	C4532X5R1H685K	4.50±0.40	3.20±0.40	2.50±0.30		0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
344	C4532X5R1E106K	4.50±0.40	3.20±0.40	2.50±0.30		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
345	C4532X5R1E156M	4.50±0.40	3.20±0.40	2.80±0.30		0.05	120Hz	0.5Vrms	±12.5%	±25%	±25%	±25%	20 x R.V.	Plastic	500	2,000		
346	C4532X5R1E226M	4.50±0.40	3.20±0.40	2.50±0.30		0.03	120Hz	0.5Vrms	±12.5%	±25%	±25%	±25%	20 x R.V.	Plastic	500	3,000		
347	C4532X5R1C336M	4.50±0.40	3.20±0.40	2.50±0.30		0.05	120Hz	0.5Vrms	±12.5%	±25%	±25%	±25%	20 x R.V.	Plastic	500	3,000		
348	C4532X5R1A476M	4.50±0.40	3.20±0.40	2.80±0.30		0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	2,000		
349	C4532X5R0J107M	4.50±0.40	3.20±0.40	2.80±0.30		0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	2,000		
350	C4532X7R1H225K	4.50±0.40	3.20±0.40	1.60±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	1,000	3,000		
351	C4532X7R1H335K	4.50±0.40	3.20±0.40	2.00±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	1,000	3,000		
352	C4532X7R1H475K	4.50±0.40	3.20±0.40	2.00±0.20		0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	1,000	3,000		
353	C4532X7R1H685K	4.50±0.40	3.20±0.40	2.50±0.30		0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	500	3,000		
354	C4532X7R1E106K	4.50±0.40	3.20±0.40	2.50±0.30		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
355	C4532X7R1E156M	4.50±0.40	3.20±0.40	2.80±0.30		0.05	120Hz	0.5Vrms	±12.5%	±25%	±25%	±25%	15 x R.V.	Plastic	500	2,000		
356	C4532X7R1E226M	4.50±0.40	3.20±0.40	2.50±0.30		0.03	120Hz	0.5Vrms	±12.5%	±25%	±25%	±25%	R.V.	Plastic	500	3,000		
357	C4532X7R1C226M	4.50±0.40	3.20±0.40	2.30±0.20		0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	500	3,000		
358	C4532X7R1C336M	4.50±0.40	3.20±0.40	2.50±0.30		0.05	120Hz	0.5Vrms	±12.5%	±25%	±25%	±25%	R.V.	Plastic	500	3,000		
359	C4532Y5V1A107Z	4.50±0.40	3.20±0.40	2.50±0.30		0.125	120Hz	0.5Vrms	±20%	±30%	±30%	±30%	20 x R.V.	Plastic	500	3,000		
360	C5750X5R1H106K	5.70±0.40	5.00±0.40	2.30±0.20		0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
361	C5750X5R1E156M	5.70±0.40	5.00±0.40	2.30±0.20		0.03	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
362	C5750X5R1E226M	5.70±0.40	5.00±0.40	2.30±0.20		0.05	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
363	C5750X5R1C336M	5.70±0.40	5.00±0.40	2.00±0.20		0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
364	C5750X5R1C476M	5.70±0.40	5.00±0.40	2.30±0.20		0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
365	C5750X5R1A686M	5.70±0.40	5.00±0.40	2.30±0.20		0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
366	C5750X7R1H475K	5.70±0.40	5.00±0.40	2.00±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
367	C5750X7R1H685K	5.70±0.40	5.00±0.40	2.50±0.30		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
368	C5750X7R1H106K	5.70±0.40	5.00±0.40	2.30±0.20		0.05	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	500	3,000		
369	C5750X7R1E156M	5.70±0.40	5.00±0.40	2.30±0.20		0.03	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
370	C5750X7R1E226M	5.70±0.40	5.00±0.40	2.50±0.30		0.03	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	500	3,000		
371	C5750X7R1C336M	5.70±0.40	5.00±0.40	2.00±0.20		0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	500	3,000		
372	C5750X7R1C476M	5.70±0.40	5.00±0.40	2.30±0.20		0.075	120Hz	0.5Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	500	3,000		
373	C5750Y5V1H226Z	5.70±0.40	5.00±0.40	2.00±0.20		0.05	120Hz	0.5Vrms	±20%	±30%	±30%	±30%	20 x R.V.	Plastic	500	3,000		
374	C5750Y5V1E476Z	5.70±0.40	5.00±0.40	2.00±0.20		0.075	120Hz	0.5Vrms	±20%	±30%	±30%	±30%	20 x R.V.	Plastic	500	3,000		
375	C5750Y5V1C107Z	5.70±0.40	5.00±0.40	2.50±0.30		0.10	120Hz	0.5Vrms	±20%	±30%	±30%	±30%	20 x R.V.	Plastic	500	3,000		
376	C1608C0G2A101J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
377	C1608C0G2A121J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
378	C1608C0G2A151J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
379	C1608C0G2A181J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
380	C1608C0G2A221J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
381	C1608C0G2A271J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
382	C1608C0G2A331J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
383	C1608C0G2A391J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
384	C1608C0G2A471J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
385	C1608C0G2A561J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
386	C1608C0G2A681J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
387	C1608C0G2A821J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
388	C1608C0G2A102J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		
389	C1608C0G2A122J	1.60±0.10	0.80±0.10	0.80±0.10	1.000		1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000		

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.		Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life		Tape packaging materials	Qty. per 1 reel	
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage				ΔC/C	ΔC/C	ΔC/C	Test voltage	φ178mm
390	C1608CG2E101J	1.60±0.10	0.80±0.10	0.80±0.10	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
391	C1608CG2E121J	1.60±0.10	0.80±0.10	0.80±0.10	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
392	C1608CG2E151J	1.60±0.10	0.80±0.10	0.80±0.10	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
393	C1608CG2E181J	1.60±0.10	0.80±0.10	0.80±0.10	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
394	C1608CG2E221J	1.60±0.10	0.80±0.10	0.80±0.10	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
395	C1608CG2E271J	1.60±0.10	0.80±0.10	0.80±0.10	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
396	C1608CG2E331J	1.60±0.10	0.80±0.10	0.80±0.10	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
397	C1608CG2E391J	1.60±0.10	0.80±0.10	0.80±0.10	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
398	C1608CG2E471J	1.60±0.10	0.80±0.10	0.80±0.10	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
399	C1608CG2E561J	1.60±0.10	0.80±0.10	0.80±0.10	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
400	C1608CG2E681J	1.60±0.10	0.80±0.10	0.80±0.10	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
401	C2012CG2A152J	2.00±0.20	1.25±0.20	0.60±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000
402	C2012CG2A182J	2.00±0.20	1.25±0.20	0.85±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000
403	C2012CG2A222J	2.00±0.20	1.25±0.20	0.85±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000
404	C2012CG2A272J	2.00±0.20	1.25±0.20	1.25±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	2,000	10,000
405	C2012CG2A332J	2.00±0.20	1.25±0.20	1.25±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	2,000	10,000
406	C2012CG2A392J	2.00±0.20	1.25±0.20	1.25±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	2,000	10,000
407	C2012CG2A472J	2.00±0.20	1.25±0.20	1.25±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	2,000	10,000
408	C2012CG2E821J	2.00±0.20	1.25±0.20	0.60±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
409	C2012CG2E102J	2.00±0.20	1.25±0.20	0.85±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
410	C2012CG2E122J	2.00±0.20	1.25±0.20	0.85±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000
411	C2012CG2E152J	2.00±0.20	1.25±0.20	0.85±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
412	C2012CG2E182J	2.00±0.20	1.25±0.20	1.25±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	2,000	10,000
413	C2012CG2E222J	2.00±0.20	1.25±0.20	1.25±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	2,000	10,000
414	C2012CG2E272J	2.00±0.20	1.25±0.20	1.25±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	2,000	10,000
415	C3216CG2A562J	3.20±0.20	1.60±0.20	0.85±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Paper	4,000	10,000
416	C3216CG2A682J	3.20±0.20	1.60±0.20	1.15±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	2,000	10,000
417	C3216CG2A822J	3.20±0.20	1.60±0.20	1.15±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	2,000	10,000
418	C3216CG2A103J	3.20±0.20	1.60±0.20	1.15±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	2,000	10,000
419	C3216CG2E332J	3.20±0.20	1.60±0.20	0.85±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Paper	4,000	10,000
420	C3216CG2E392J	3.20±0.20	1.60±0.20	1.15±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	2,000	10,000
421	C3216CG2E472J	3.20±0.20	1.60±0.20	1.15±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	2,000	10,000
422	C3216CG2E562J	3.20±0.20	1.60±0.20	1.15±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	2,000	10,000
423	C3216CG2E682J	3.20±0.20	1.60±0.20	1.60±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	2,000	8,000
424	C3216CG2E822J	3.20±0.20	1.60±0.20	1.60±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	2,000	8,000

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.		Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life			Tape packaging materials	Qty. per 1 reel	
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage				ΔC/C	ΔC/C	ΔC/C	Test voltage	φ178mm	φ330mm
425	C3216CG2J101J	3.20±0.20	1.60±0.20	0.60±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
426	C3216CG2J121J	3.20±0.20	1.60±0.20	0.60±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
427	C3216CG2J151J	3.20±0.20	1.60±0.20	0.60±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
428	C3216CG2J181J	3.20±0.20	1.60±0.20	0.60±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
429	C3216CG2J221J	3.20±0.20	1.60±0.20	0.60±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
430	C3216CG2J271J	3.20±0.20	1.60±0.20	0.60±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
431	C3216CG2J331J	3.20±0.20	1.60±0.20	0.60±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
432	C3216CG2J391J	3.20±0.20	1.60±0.20	0.60±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
433	C3216CG2J471J	3.20±0.20	1.60±0.20	0.85±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
434	C3216CG2J561J	3.20±0.20	1.60±0.20	0.85±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
435	C3216CG2J681J	3.20±0.20	1.60±0.20	0.85±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
436	C3216CG2J821J	3.20±0.20	1.60±0.20	0.85±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
437	C3216CG2J102J	3.20±0.20	1.60±0.20	0.85±0.15	1,000			1MHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
438	C3216CG2J122J	3.20±0.20	1.60±0.20	0.85±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Paper	4,000	10,000	
439	C3216CG2J152J	3.20±0.20	1.60±0.20	1.15±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	2,000	10,000	
440	C3216CG2J182J	3.20±0.20	1.60±0.20	1.15±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	2,000	10,000	
441	C3216CG2J222J	3.20±0.20	1.60±0.20	1.15±0.15	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	2,000	10,000	
442	C3216CG2J272J	3.20±0.20	1.60±0.20	1.60±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	2,000	8,000	
443	C3216CG2J332J	3.20±0.20	1.60±0.20	1.60±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	2,000	8,000	
444	C3225CG2A153K	3.20±0.40	2.50±0.30	1.25±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	2,000	8,000	
445	C3225CG2A223K	3.20±0.40	2.50±0.30	1.60±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	2,000	8,000	
446	C3225CG2A333K	3.20±0.40	2.50±0.30	2.00±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	1,000	5,000	
447	C3225CG2A473K	3.20±0.40	2.50±0.30	2.30±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	1,000	5,000	
448	C3225CG2E103J	3.20±0.40	2.50±0.30	1.60±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	2,000	8,000	
449	C3225CG2E153K	3.20±0.40	2.50±0.30	2.00±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	1,000	5,000	
450	C3225CG2J392J	3.20±0.40	2.50±0.30	1.25±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	2,000	8,000	
451	C3225CG2J472J	3.20±0.40	2.50±0.30	1.60±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	2,000	8,000	
452	C3225CG2J562J	3.20±0.40	2.50±0.30	1.60±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	2,000	8,000	
453	C3225CG2J682J	3.20±0.40	2.50±0.30	2.00±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	1,000	5,000	
454	C4532CG2A683K	4.50±0.40	3.20±0.40	2.50±0.30	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	500	3,000	
455	C4532CG2A104K	4.50±0.40	3.20±0.40	3.20±0.40	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	20 x R.V.	Plastic	500	2,000	
456	C4532CG2E223K	4.50±0.40	3.20±0.40	1.60±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	1,000	3,000	
457	C4532CG2E333K	4.50±0.40	3.20±0.40	2.00±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	1,000	3,000	
458	C4532CG2E473K	4.50±0.40	3.20±0.40	3.20±0.40	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	15 x R.V.	Plastic	500	2,000	
459	C4532CG2J622J	4.50±0.40	3.20±0.40	1.60±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	1,000	3,000	
460	C4532CG2J103J	4.50±0.40	3.20±0.40	1.60±0.20	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	1,000	3,000	
461	C4532CG2J153K	4.50±0.40	3.20±0.40	2.50±0.30	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	500	3,000	
462	C4532CG2J223K	4.50±0.40	3.20±0.40	3.20±0.40	1,000			1kHz	0.5-5Vrms	±2.5%	±5.0%	±7.5%	±3.0%	12 x R.V.	Plastic	500	2,000	

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.		Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life			Tape packaging materials	Qty. per 1 reel	
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage				ΔC/C	ΔC/C	ΔC/C	Test voltage	φ178mm	φ330mm
463	C1608X7R2A102K	1.60±0.10	0.80±0.10	0.80±0.10		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Paper	4,000	10,000		
464	C1608X7R2A152K	1.60±0.10	0.80±0.10	0.80±0.10		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Paper	4,000	10,000		
465	C1608X7R2A222K	1.60±0.10	0.80±0.10	0.80±0.10		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Paper	4,000	10,000		
466	C1608X7R2A332K	1.60±0.10	0.80±0.10	0.80±0.10		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Paper	4,000	10,000		
467	C1608X7R2A472K	1.60±0.10	0.80±0.10	0.80±0.10		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Paper	4,000	10,000		
468	C1608X7R2A682K	1.60±0.10	0.80±0.10	0.80±0.10		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Paper	4,000	10,000		
469	C1608X7R2A103K	1.60±0.10	0.80±0.10	0.80±0.10		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Paper	4,000	10,000		
470	C1608X7R2A153K	1.60±0.10	0.80±0.10	0.80±0.10		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Paper	4,000	10,000		
471	C1608X7R2A223K	1.60±0.10	0.80±0.10	0.80±0.10		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Paper	4,000	10,000		
472	C2012X7R2A333K	2.00±0.20	1.25±0.20	1.25±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	2,000	10,000		
473	C2012X7R2A473K	2.00±0.20	1.25±0.20	1.25±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	2,000	10,000		
474	C2012X7R2A683K	2.00±0.20	1.25±0.20	0.85±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Paper	4,000	10,000		
475	C2012X7R2A104K	2.00±0.20	1.25±0.20	1.25±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	2,000	10,000		
476	C2012X7R2E102K	2.00±0.20	1.25±0.20	0.85±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Paper	4,000	10,000		
477	C2012X7R2E152K	2.00±0.20	1.25±0.20	0.85±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Paper	4,000	10,000		
478	C2012X7R2E222K	2.00±0.20	1.25±0.20	0.85±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Paper	4,000	10,000		
479	C2012X7R2E332K	2.00±0.20	1.25±0.20	0.85±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Paper	4,000	10,000		
480	C2012X7R2E472K	2.00±0.20	1.25±0.20	0.85±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Paper	4,000	10,000		
481	C2012X7R2E682K	2.00±0.20	1.25±0.20	1.25±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	2,000	10,000		
482	C2012X7R2E103K	2.00±0.20	1.25±0.20	1.25±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	2,000	10,000		
483	C2012X7R2E153K	2.00±0.20	1.25±0.20	1.25±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	2,000	10,000		
484	C2012X7R2E223K	2.00±0.20	1.25±0.20	1.25±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	2,000	10,000		
485	C3216X7R2A154K	3.20±0.20	1.60±0.20	1.60±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	2,000	8,000		
486	C3216X7R2A224K	3.20±0.20	1.60±0.20	1.15±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	2,000	10,000		
487	C3216X7R2A334K	3.20±0.20	1.60±0.20	1.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	2,000	10,000		
488	C3216X7R2A474K	3.20±0.20	1.60±0.20	1.60±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	2,000	8,000		
489	C3216X7R2A105K	3.20±0.20	1.60±0.20	1.60±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	20 x R.V.	Plastic	2,000	8,000		
490	C3216X7R2E333K	3.20±0.20	1.60±0.20	1.60±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	2,000	8,000		
491	C3216X7R2E473K	3.20±0.20	1.60±0.20	1.60±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	2,000	8,000		
492	C3216X7R2E683K	3.20±0.20	1.60±0.20	1.60±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	2,000	8,000		
493	C3216X7R2E104K	3.20±0.20	1.60±0.20	1.60±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	15 x R.V.	Plastic	2,000	8,000		
494	C3216X7R2J102K	3.20±0.20	1.60±0.20	1.15±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	12 x R.V.	Plastic	2,000	10,000		
495	C3216X7R2J152K	3.20±0.20	1.60±0.20	1.15±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	12 x R.V.	Plastic	2,000	10,000		
496	C3216X7R2J222K	3.20±0.20	1.60±0.20	1.15±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	12 x R.V.	Plastic	2,000	10,000		
497	C3216X7R2J332K	3.20±0.20	1.60±0.20	1.15±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	12 x R.V.	Plastic	2,000	10,000		
498	C3216X7R2J472K	3.20±0.20	1.60±0.20	1.15±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	12 x R.V.	Plastic	2,000	10,000		
499	C3216X7R2J682K	3.20±0.20	1.60±0.20	1.15±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	12 x R.V.	Plastic	2,000	10,000		
500	C3216X7R2J103K	3.20±0.20	1.60±0.20	1.15±0.15		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	12 x R.V.	Plastic	2,000	10,000		
501	C3216X7R2J153K	3.20±0.20	1.60±0.20	1.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	12 x R.V.	Plastic	2,000	10,000		
502	C3216X7R2J223K	3.20±0.20	1.60±0.20	1.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	12 x R.V.	Plastic	2,000	10,000		
503	C3216X7R2J333K	3.20±0.20	1.60±0.20	1.60±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	12 x R.V.	Plastic	2,000	8,000		

No	Your Part No.	TDK product	Dimensions			Q (min.)	tanδ (max.)	Temp. Characteristics of Cap.		Temp cycle	Moisture Resistance (Steady state)	Moisture Resistance	Life			Tape packaging materials	Qty. per 1 reel	
			L (mm)	W (mm)	T (mm)			Measuring frequency	Measuring voltage				ΔC/C	ΔC/C	ΔC/C	Test voltage	φ178mm	φ330mm
504	C3225X7R2A684K	3.20±0.40	2.50±0.30	1.60±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	2.0 x R.V.	Plastic	2,000	8,000		
505	C3225X7R2A105K	3.20±0.40	2.50±0.30	2.00±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	2.0 x R.V.	Plastic	1,000	5,000		
506	C3225X7R2A225K	3.20±0.40	2.50±0.30	2.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	1.5 x R.V.	Plastic	1,000	5,000		
507	C3225X7R2E154K	3.20±0.40	2.50±0.30	2.00±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	1.5 x R.V.	Plastic	1,000	5,000		
508	C3225X7R2E224K	3.20±0.40	2.50±0.30	2.00±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	1.5 x R.V.	Plastic	1,000	5,000		
509	C3225X7R2E473K	3.20±0.40	2.50±0.30	2.00±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	1.2 x R.V.	Plastic	1,000	5,000		
510	C3225X7R2J683K	3.20±0.40	2.50±0.30	2.00±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	1.2 x R.V.	Plastic	1,000	5,000		
511	C4532X7R2A155K	4.50±0.40	3.20±0.40	2.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	2.0 x R.V.	Plastic	500	3,000		
512	C4532X7R2A225K	4.50±0.40	3.20±0.40	2.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	2.0 x R.V.	Plastic	500	3,000		
513	C4532X7R2E334K	4.50±0.40	3.20±0.40	2.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	1.5 x R.V.	Plastic	500	3,000		
514	C4532X7R2E474K	4.50±0.40	3.20±0.40	2.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	1.5 x R.V.	Plastic	500	3,000		
515	C4532X7R2J104K	4.50±0.40	3.20±0.40	2.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	1.2 x R.V.	Plastic	500	3,000		
516	C5750X7R2A335K	5.70±0.40	5.00±0.40	2.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	2.0 x R.V.	Plastic	500	3,000		
517	C5750X7R2A475K	5.70±0.40	5.00±0.40	2.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	2.0 x R.V.	Plastic	500	3,000		
518	C5750X7R2E684K	5.70±0.40	5.00±0.40	2.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	1.5 x R.V.	Plastic	500	3,000		
519	C5750X7R2E105K	5.70±0.40	5.00±0.40	2.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	1.5 x R.V.	Plastic	500	3,000		
520	C5750X7R2J154K	5.70±0.40	5.00±0.40	1.60±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	1.2 x R.V.	Plastic	1,000	3,000		
521	C5750X7R2J224K	5.70±0.40	5.00±0.40	2.30±0.20		0.03	1kHz	1.0Vrms	±7.5%	±12.5%	±12.5%	±15%	1.2 x R.V.	Plastic	500	3,000		

Note:

Table A lists the TDK part number offering and the applicable guaranteed specifications. Please contact your TDK sales representative for product availability