



## SURMOUNT™ Low Barrier 0201 Footprint Silicon Schottky Diodes

MA4E2501-1290 Series V1

#### **Features**

- Extremely Low Parasitic Capitance and Inductance
- Extremely Small 0201 (600x300um) Footprint
- Surface Mountable in Microwave Circuits, No Wirebonds Required
- Rugged HMIC Construction with Polyimide Scratch Protection
- Reliable, Multilayer Metalization with a Diffusion Barrier, 100% Stabilization Bake (300 °C, 16 hours)
- Lower Susceptibility to ESD Damage

## **Description and Applications**

The MA4E2501L-1290 SurMount™ Diodes are Silicon Low Barrier Schottky Devices fabricated with the patented Heterolithic Microwave Integrated Circuit (HMIC) process. HMIC circuits consist of Silicon pedestals which form diodes or via conductors embedded in a glass dielectric, which acts as the low dispersion, microstrip transmission medium. The combination of silicon and glass allows HMIC devices to have excellent loss and power dissipation characteristics in a low profile, reliable device.


The Surmount Schottky devices are excellent choices for circuits requiring the small parasitics of a beam lead device coupled with the superior mechanical performance of a chip. The SurMount structure employs very low resistance silicon vias to connect the Schottky contacts to the metalized mounting pads on the bottom surface of the chip. These devices are reliable, repeatable, and a lower cost performance solution to conventional devices. They have lower susceptibility to electrostatic discharge than conventional beam lead Schottky diodes.

The multi-layer metalization employed in the fabrication of the Surmount Schottky junctions includes a platinum diffusion barrier, which permits all devices to be subjected to a 16-hour non-operating stabilization bake at 300°C.

The extremely small "0201" outline allows for Surface Mount placement and multi-functional polarity orientations.

The MA4E2501L-1290 SurMount Low Barrier Schottky diodes are recommended for use in microwave circuits through Ku band frequencies for lower power applications such as mixers, sub-harmonic mixers, detectors and limiters. The HMIC construction facilitates the direct replacement of more fragile beam lead diodes with the corresponding Surmount diode, which can be connected to a hard or soft substrate circuit with solder.

### Case Style 1290



	Inch	ies	Millimeters			
Dim	Min.	Max.	Min.	Max.		
Α	0.023	0.025	0.575	0.625		
В	0.011	0.013	0.275	0.325		
С	0.004	0.008	0.102	0.203		
D	0.006	0.008	0.150	0.200		
E	0.007	0.009	0.175	0.225		
F	0.006	0.008	0.150	0.200		
G	0.009	0.011	0.220	0.270		

- North America Tel: 800.366.2266 / Fax: 978.366.2266
  - **Europe** Tel: 44.1908.574.200 / Fax: 44.1908.574.300
  - Asia/Pacific Tel: 81.44.844.8296 / Fax: 81.44.844.8298

M/A-COM Inc. and its affiliates reserve the right to make changes to the product(s) or information contained herein without notice. M/A-COM makes no warranty, representation or guarantee regarding the suitability of its products for any particular purpose, nor does M/A-COM assume any liability whatsoever arising out of the use or application of any product(s) or information.

Visit www.macom.com for additional data sheets and product information.





## **SURMOUNT™** Low Barrier 0201 Footprint Silicon Schottky Diodes

MA4E2501-1290 Series V1

### Electrical Specifications @ 25 °C

Model Number	Туре	Recommended Frequency Range	Vf @ 1 mA ( mV )	Vb @ 10 uA (V)	Ct @ 0V (pF)	Rt Slope Resistance ( Vf1 - Vf2 )/(10.5mA-9.5mA ) ( $\Omega$ )
MA4E2501L-	Low	DC - 18 GHz	330 Max	3 Min	0.12 Max	10 Typ
1290	Barrier		300 Typ	5 Typ	0.10 Typ	14 Max

Rt is the dynamic slope resistance where Rt = Rs + Rj, where Rj = 26 / Idc (Idc is in mA)

#### Handling

All semiconductor chips should be handled with care to avoid damage or contamination from perspiration and skin oils. The use of plastic tipped tweezers or vacuum pickups is strongly recommended for individual components. The top surface of the die has a protective polyimide coating to minimize damage.

The rugged construction of these SurMount devices allows the use of standard handling and die attach techniques. It is important to note that industry standard electrostatic discharge (ESD) control is required at all times, due to the sensitive nature of Schottky junctions.

Bulk handling should insure that abrasion and mechanical shock are minimized.

## Absolute Maximum Ratings @ 25 °C (Unless Otherwise Noted) 1

Parameter	Absolute Maximum
Operating Temperature	-40 °C to +150 °C
Storage Temperature	-40 °C to +150 °C
Forward Current	20 mA
Reverse Voltage	5 V
RF C.W. Incident Power	+ 20 dBm
RF & DC Dissipated Power	50 mW

1. Operation of this device above any one of these parameters may cause permanent damage.

#### Die Bonding

Die attach for these devices is made simple through the use of surface mount die attach technology. Mounting pads are conveniently located on the bottom surface of these devices, and are opposite the active junction. The devices are well suited for higher temperature solder attachment onto hard substrates. 80Au/20Sn and Sn63/Pb37 solders are acceptable for usage. Die attach with Electrically Conductive Silver Epoxy is Not Recommended.

For Hard substrates, we recommend utilizing a vacuum tip and force of 60 to 100 grams applied uniformly to the top surface of the device, using a hot gas bonder with equal heat applied across the bottom mounting pads of the device. When soldering to soft substrates, it is recommended to use a lead-tin interface at the circuit board mounting pads. Position the die so that its mounting pads are aligned with the circuit board mounting pads. Reflow the solder paste by applying Equal heat to the circuit at both die-mounting pads. The solder joint must Not be made one at a time, creating un-equal heat flow and thermal stress. Solder reflow should Not be performed by causing heat to flow through the top surface of the die. Since the HMIC glass is transparent, the edges of the mounting pads can be visually inspected through the die after die attach is completed.

M/A-COM Inc. and its affiliates reserve the right to make changes to the

no warranty, representation or guarantee regarding the suitability of its

product(s) or information contained herein without notice. M/A-COM makes

products for any particular purpose, nor does M/A-COM assume any liability whatsoever arising out of the use or application of any product(s) or

Visit www.macom.com for additional data sheets and product information.

INUITE ATTICITED TOTA OUU.SUU.ZZUU / T AA. 37 0.SUU.ZZUU

**Europe** Tel: 44.1908.574.200 / Fax: 44.1908.574.300

Asia/Pacific Tel: 81.44.844.8296 / Fax: 81.44.844.8298






# **SURMOUNT™** Low Barrier 0201 Footprint Silicon Schottky Diodes

MA4E2501-1290 Series V1


#### MA4E2501L-1290 Low Barrier SPICE PARAMETERS

ls (nA)	Rs (Ω)	N	Cj0 ( pF )	M	lk (mA)	Cjpar (pF)	Vj (V)	FC	BV (V)	IBV (mA)
26	12.8	1.20	1.0 E-2	0.5	14	9.0 E-2	8.0 E-2	0.5	5.0	1.0 E-2

## **Typical Performance**



## **Circuit Mounting Dimensions (Inches)**



## **Ordering Information**

Part Number	Package				
MA4E2501L-1290W	Wafer on Frame				
MA4E2501L-1290	Die in Carrier				
MA4E2501L-1290T	Tape/Reel				

M/A-COM Inc. and its affiliates reserve the right to make changes to the product(s) or information contained herein without notice. M/A-COM makes no warranty, representation or guarantee regarding the suitability of its products for any particular purpose, nor does M/A-COM assume any liability whatsoever arising out of the use or application of any product(s) or information.

<sup>•</sup> North America Tel: 800.366.2266 / Fax: 978.366.2266

<sup>•</sup> Europe Tel: 44.1908.574.200 / Fax: 44.1908.574.300

Asia/Pacific Tel: 81.44.844.8296 / Fax: 81.44.844.8298